

## Dielectric relaxation of polymer composites based on a MF-4SK membrane and polyantimonic acid

© Fedor A. Yaroshenko,<sup>+</sup> Vladimir A. Burmistrov,<sup>\*</sup> and Kirill S. Makarov

Department of Solid State Chemistry and Nanoprocesses. Chelyabinsk State University.

Brat'ev Kashirinykh St., 129. Chelyabinsk, 454001. Phone: +7 (351) 799 70 63, +7 (9630) 92-83-27.

E-mail: burmistrov@csu.ru; fedor\_yaroshenko@mail.ru

\*Supervising author; <sup>+</sup>Corresponding author

**Keywords:** proton conductivity, polymeric membranes, antimony compounds, impedance spectroscopy, dielectric relaxation.

### Abstract

This paper presents the results of studies of composite membranes based on MF-4SK and polyantimonic acid (PAA) with the composition  $H(H_3O)Sb_2O_6 \cdot H_2O \cdot 0.2H_2O$ . Composite membranes were prepared by mixing disperse PAA and aqueous solution of MF-4SK in ratios of MF-4SK+3% PAA. After having been dried under the normal conditions, the samples represented elastic films with a thickness of 120-150 microns.

Dielectric characteristics of PAA were measured by a complex impedance spectroscopy technique in the frequency range from 100 Hz to 2 MHz on an *ElinsZ-1500J* impedance analyzer. We used a purpose-designed cell in the form of a flat capacitor with graphite electrodes. The sample to be studied was placed into the space between the electrodes. The cell was placed in a thermostat, which allowed the sample temperature to be varied from 220 to 300 K.

Processes related to the relaxation and proton transport in a heterogeneous system were considered. Thus, the frequency dependences of the dielectric loss tangent and of the imaginary part of permittivity at various temperatures display peaks that shift towards the higher frequency side with rise in temperature.

Cole-Cole diagrams of the MF-4SK + 3% PAA samples at different temperatures represent semicircular arcs resting on the segments ( $\varepsilon_s - \varepsilon_\infty$ ) with their centers positioned below the x-axis. This indicates that within the sample to be studied the processes having a range of relaxation time and with an average relaxation time  $\tau_c$  occur. The static dielectric permittivity at different temperatures was derived from above diagram. Large  $\varepsilon_s$  values indicate the inhomogeneous structure of the dielectric membrane and the macrodipole formation.

The proton transport in the composite membranes has been shown to occur both within a PAA particle along the chains of alternating diaquahydrogen ions with the formation of macrodipoles and in the polymer matrix MF-4SK. The conductivity activation energy results from the change in the mobility and concentration of protons involved in charge transport and amounts to 48 kJ/mol.

### References

- [1] A.B. Yaroslavl'tsev. Perfluorinated ion-exchange membranes. *Polymer Science. Series A*. **2013**. Vol.55. No.11. P.674-698.
- [2] F. Lufrano, G. Squadrito, A. Patti, E. Passalacqua. Sulfonated polysulfone as promising membranes for polymer electrolyte fuel cells. *J. Appl. Polym. Sci.* **2000**. Vol.77. Iss.6. P.1250-1256.
- [3] F. Trotta, E. Drioli, G. Moraglio, E.B. Poma. Sulfonation of polyetheretherketone by chlorosulfuric acid. *J. Polym. Sci.* **1998**. Vol.70. Iss.3. P.477-482.
- [4] V.A. Burmistrov, N.E. Adrianova, V.Yu. Ryabishev, Yu.M. Ryabishev. Changes in the structure of the hydrate of antimony pentoxide in ion exchange and thermolysis it replaced Ag,H-forms. *Inorganic Materials*. **1997**. Vol.33. No.12. P.1475-1477. (russian)
- [5] V.A. Burmistrov, D.A. Saharevishch, D.G. Kleshev. Structure and chemical transformations during the thermolysis Me, H-form crystal poliantimonic acid (Me-Ba, Pb). *Journal of Inorganic Chemistry*. **2001**. Vol.46. No.12. P.1946-1949. (russian)
- [6] B.G. Polevoy, V.A. Burmistrov, E.I. Burmakin. The proton conductivity of the hydrate of antimony pentoxide. *News AS USSR, Inorganic Materials*. **1991**. Vol.27. No.12. P.2584-2586. (russian)
- [7] L.Yu. Kovalenko, V.A. Burmistrov, A.A. Biryukova. Kinetics of H<sup>+</sup>/Me<sup>+</sup> (Me = Na, K) Ion Exchange in Polyantimonic Acid. *Russian Journal of Electrochemistry*. **2016**. Vol.52. No.7. P.694-698.

- [8] X. Glipa, M.E. Haddad, D.J. Jones, J. Roziere. Synthesis and characterisation of sulfonated polybenzimidazole: a highly conducting proton exchange polymer. *Solid State Ionics*. **1997**. Vol.97. Iss.1-4. P.323-331.
- [9] K.D. Kreuer, M. Hampele, L. Dolde, A. Rabenau. Proton transport in some heteropolyacidhydrates a single crystal PFG-NMR and conductivity study. *Solid State Ionics*. **1988**. Vol.28-30. P.589-593.
- [10] T.S. Chung. A Critical Review of Polybenzimidazoles. *J. Macromol. Sci.* **1997**. Vol.37. Iss.2. P.277-301.
- [11] A.B. Yaroslavtsev, V.V. Nikonenko, V.I. Zabolotsky. Ion transfer in ion-exchange and membrane materials. *Russian Chemical Reviews*. **2003**. Vol.72. No.5. P.393-421.
- [12] V.A. Burmistrov, V.M. Chernov, R.I. Valeev, N.E. Adrianova. The transfer of protons in the hydrate of antimony pentoxide. *Inorganic Materials*. **1998**. Vol.34. No.5. P.1-4. (russian)
- [13] A.B. Yaroslavtsev. The main directions of development and research of solid electrolytes. *Russian Chemical Reviews*. **2016**. Vol.85. No.11. P.1255-1276. (russian)
- [14] Zhi-Gang Shao, Hongfeng Xu, Mingqiang Li, I-Ming Hsing Hybrid Nafion–inorganic oxides membrane doped with heteropolyacids for high temperature operation of proton exchange membrane fuel cell. *Solid State Ionics*. **2006**. Vol.177. Iss.7-8. P.779-785.
- [15] L.H. Batsle, D. Huys. Structure and Ion-exchange Characteristics of Polyantymonic. *Acid J. Inorg. Nucl. Chem.* **1968**. Vol.30. Iss.2. P.639-649.
- [16] D. Klestchov, V. Burmistrov, A. Sheinkman, R. Pletnev. Composition and structure of phases formed in the process of hydrated antimony pentoxide thermolysis. *J. Solid State Chem.* **1991**. Vol.94. Iss.2. P.220-226.
- [17] A.A. Bauer, D.G. Kleshchev, V.A. Burmistrov, V.N. Konev, G.V. Kleshchev. X-graphic studies Me, H-form of the hydrate of antimony pentoxide. *Journal of Inorganic Chemistry*. **1984**. Vol.20. No.10. P.2471-2475. (russian)
- [18] V.A. Burmistrov, D.G. Kleshchev, V.N. Konev, R.N. Pletnev. The state of the protons in the hydrate of antimony pentoxide. *DAS USSR*. **1981**. Vol.261. No.2. P.366-368. (russian)
- [19] V.A. Burmistrov, V.M. Chernov, R.I. Valeev. The transfer of protons in the hydrate of antimony pentoxide. *Inorganic Materials*. **1998**. Vol.34. No.5. P.1-4. (russian)
- [20] B.G. Polevoy, V.A. Burmistrov, E.I. Burmakin. The proton conductivity of the hydrate of antimony pentoxide. *News AS USSR. Inorganic Materials*. **1991**. Vol.27. No.12. P.2584-2586. (russian)
- [21] V.A. Burmistrov, D.G. Kleshchev, V.N. Konev, G.V. Kleshchev. The transformation of the hydrate of antimony pentoxide when heated. *News AS USSR. Inorganic Materials*. **1982**. Vol.18. No.1. P.91-93. (russian)
- [22] V.A. Burmistrov, D.G. Kleshchev, V.N. Konev, R.N. Pletnev. The change in the proton structure of the hydrate of antimony pentoxide during thermolysis and ion exchange. *Journal of Inorganic Chemistry*. **1985**. Vol.30. No.8. P.1959-1963. (russian)
- [23] V.A. Burmistrov, Yu.M. Ryabishev, N.I. Shmonkina. Phase transformations ionozameshchennykh forms of the hydrate of antimony pentoxide. *News AS USSR, Inorganic materials*. **1991**. Vol.27. No.1. P.50-52. (russian)
- [24] V.A. Burmistrov, Yu.M. Ryabishev, V.Yu. Ryabishev. Thermolysis of the hydrate of antimony pentoxide in a first stage recovery of Sb(V) to Sb(III). *Journal of Inorganic Chemistry*. **1996**. Vol. 41. No.5. P.737-738. (russian)
- [25] D.G. Kleshchev, A.A. Polyakov, A.V. Tolchev, V.A. Burmistrov, G.V. Kleshchev. The formation of Sb<sub>2</sub>O<sub>5</sub> during thermolysis of the hydrate of antimony pentoxide in a closed system. *News AS USSR, Inorganic Materials*. **1983**. Vol.19. No.9. P.1505-1507. (russian)
- [26] F.A. Yaroshenko, V.A. Burmistrov Proton Conductivity of Polyantimonic Acid Studied by Impedance Spectroscopy in the Temperature Range 370-480 K. *Inorganic Materials*. **2015**. Vol.51. No.8. P.783-787.
- [27] V.A. Burmistrov. Structure, ion exchange and proton conductivity poliantimonic crystalline acid. *Chelyabinsk: Chelyabinsk. State. Univ.* **2010**. 247p. (russian)
- [28] F.A. Yaroshenko, V.A. Burmistrov. Dielectric Relaxation and Protonic Conductivity of Polyantimonic Crystalline Acid at Low Temperatures. *Russian Journal of Electrochemistry*. **2015**. Vol.51. No.5. P.391-396.
- [29] F.A. Yaroshenko, V.A. Burmistrov. Dielectric relaxation of disperse poliantimonic acid at low temperatures. *Bulletin of Chelyabinsk state University*. **2015**. No.22 (377). Physics. Vol.21. P.136-142. (russian)
- [30] F.A. Yaroshenko, V.A. Burmistrov. Dielectric losses and proton conductivity of poliantimonic acid membranes. *Russian Journal of Electrochemistry*. **2016**. Vol.52. No.7. P.690-693.