

Influence of dispersion and polymorphic modification on explosive characteristics, thermal decomposition and combustion of CL-20 and composite power materials on its basis

© Vladimir N. Popok,*⁺ Nikolay I. Popok, and Yury A. Pivovarov

Joint Stock Company "Federal Research and Production Center "Altay".

Socialistic St., 1. Biysk, 659322. Altay Kray, Russia.

Phone: +7 (3854) 30-19-37. E-mail: vnpopok@mail.ru

*Supervising author; ⁺Corresponding author

Keywords: hexanitrohexaazaisowurtzitane, CL-20, polymorphs, particle size, composite power materials, thermal decomposition, burning rate, sensitivity to mechanical influences.

Abstract

In article results of the analysis influence dispersion, including highly dispersive and nanodimensional powders, and polymorphic modifications of a hexanitrohexaazaisowurtzitane (CL-20) on explosive characteristics, thermal decomposition, burning rate and other properties of compositions are given in its basis. CL-20 (density, to an education enthalpy, an oxidation potential) surpasses such nitramines as hexogen and octogen in the power mass characteristics. However, CL-20 are inherent specific features of interaction with the majority of polar polymers, softeners and other components of the composite power materials (CPM) which complicate development, a research of properties and application of compositions with use of CL-20. It is so far established that binding on the basis of divinyl polymers are a basis of perspective compositions with CL-20. Use of such softeners, binding at the right choice, formation of complexes and cocrystals ensures safety of the polymorphic modification of CL-20 used in compositions, blocking that allows to create CPM compositions suitable for the long-lived operation.

As objects of a research the powders CL-20 of different dispersion, different polymorphic modifications received with use of methods of a crystallization without and with after-treatment by mechanical and ultrasonic influences, and also compositions on their basis are chosen. As binding the analog of polydivinyl binding (HTPB type) potentially providing required level of chemical compatibility of components, lack of polymorphic transformations and formation of complexes and cocrystal of CL-20 is chosen at manufacture and storage of compositions. The submitted data confirm lack of significant interaction of CL-20 with components of polydivinyl binding HTPB with preservation of polymorphic modification, slight solubility and lack of formation of complexes or cocrystal. After-treatment of the highly dispersive powders CL-20, transition to nanodimensional particles and molecular dispersions of CL-20 to binding allows to reduce the level of burning rate of compositions, and also to increase their safety as a result of decrease in sensitivity to mechanical influences and increases in a threshold of shock and wave sensitivity.

References

- [1] D. Lempert, G. Nechiporenko, G. Manelis. Energetic Performances of Solid Composite Propellants. *Central European Journal of Energetic Materials*. **2011**. Vol.8. No.1. P.25-38.
- [2] Xue-yong Guo, Pu Zhang, Jin-jiang XU, etc. Research on the Mechanism and Kinetics of Polymorphic Transitions of ϵ -CL-20 in Composite Systems. *Central European Journal of Energetic Materials*. **2015**. Vol.12. No.4. P.689-702.
- [3] T. Golofit, K. Zysk. Thermal decomposition properties and compatibility of CL-20 with binders HTPB, PBAN, GAP, and polyNIMMO. *J. Therm. Anal. Calorim.* **2015**. Vol.113. P.1931-1939.
- [4] S. Torry, A. Cunliffe. Polymorphism and Solubility of CL-20 in Plasticisers and Polymers. *31st International Annual Conference of ICT, Karlsruhe, Germany*. **2000**.
- [5] D. Lempert, N. Chukanov. The Outlook for the Use of Pseudopolymorphic Solvates in Energetic Materials. *Central European Journal of Energetic Materials*. **2014**. Vol.11. No.2. P. 285-294.

- [6] V.N. Popok, V.I. Desyatykh, N.I. Popok. Influence of processes of a cocrystallization on rheological and mechanical characteristics of mixes on the basis of hexanitrohexaazaisowurtzitane (HNIW). *Butlerov Communications*. **2013**. Vol.35. No.9. P.144-155. ROI: jbc-02/13-35-9-144
- [7] V.N. Popok. Effect of structural factors on burning parameters of mixed energy materials. *Butlerov Communications*. **2012**. Vol.32. No.13. P.75-87. ROI: jbc-02/12-32-13-75
- [8] V.N. Popok, N.V. Bichyn, N.I. Popok, N.V. Shein. Mechanical activation of co-crystallization of some nitro compounds. *Butlerov Communications*. **2013**. Vol.34. No.5. P.106-123. ROI: jbc-02/13-34-5-106
- [9] V.N. Popok, A.S. Zharkov. Characteristics of thermal decomposition and thermal explosion of certain components of composite energetic materials. *Butlerov Communications*. **2015**. Vol.42. No.6. P.11-16. ROI: jbc-02/15-42-6-11
- [10] A.A. Vasilieva, S.A. Dushenok, A.A. Kotomin, D.V. Dashko. Preparation and some properties of spheroidal CL-20. *Proceedings of SGTI*. **2013**. No.21(47). P.33-38. (russian)
- [11] S.N. Aponyakina, Yu.T. Lapina, I.I. Zolotychina. Crystallization of fine product CL-20. *Butlerov Communications*. **2016**. Vol.48. No.12. P.143-149. ROI: jbc-02/16-48-12-143
- [12] G.V. Teplov, N.V. Bychin, I.I. Zolotukhina, V.N. Popok. Synthesis of ultrafine CL-20 crystals by means of destruction of co-crystals on its base with some polar solvents. *Butlerov Communications*. **2017**. Vol.49. No.3. P.101-107. ROI: jbc-02/17-49-3-101
- [13] V.N. Popok, V.N. Khmelev. Composite condensed chemical fuels on the basis of ammonium nitrate. Principles of configuration and property. *Biysk: Publishing house of the Altai State Technical University*. **2014**. 222 p.(russian)
- [14] V.N. Popok, N.V. Bychin. Properties thermoreversible cocrystals with a low temperature of melting on a basis hexanitrohexaazaisowurtzitane. *Butlerov Communications*. **2014**. Vol.37. No.2. P.39-52. ROI: jbc-02/14-37-2-39
- [15] V.N. Popok, Yu.A. Pivovarov, N.I. Popok. Polymeric binding, containing hexanitrohexaazaisowurtzitane. *Butlerov Communications*. **2016**. Vol.48. No.12. P.102-108. ROI: jbc-02/16-48-12-102
- [16] V.N. Popok, N.P. Vdovina, N.V. Bychin. The compatibility of nanodispersed powders of metals and their oxides with the components of composite energetic materials. *Russian Nanotechnology*. **2013**. Vol.8. No.1-2. P.87-93. (russian)
- [17] V.N. Popok. Correlation of physical-mechanical characteristics composition power materials. *Butlerov Communications*. **2017**. Vol.49. No.3. P.135-146. ROI: jbc-02/17-49-3-135
- [18] V.N. Popok. Research on hexanitrohexaazaisowurtzitane/polymer co-crystallizate properties. *Butlerov Communications*. **2012**. Vol.30. No.6. P.132-143. ROI: jbc-02/12-30-6-132
- [19] V.N. Popok, N.I. Popok. Percolation in mixed energy materials. Characteristics of burning, ignition and sensitivity of mixtures to mechanical stress. *Butlerov Communications*. **2014**. Vol.39. No.8. P.1-16. ROI: jbc-02/14-39-8-1
- [20] B. Huang, M. Cao, F. Nie, etc. Construction and Properties of Structure and Size-controlled Micro/nano-Energetic Materials. *Defence Technology*. **2013**. No.9. P.59-79.