

Changing of mechanical properties of the pulp-and-paper material when processing his surface

© Lyaysan R. Musina,*⁺ Mansur F. Galikhanov, and Nazmieva Alsu Ildusovna

Department of Processing Technology of Plastics and Composite Materials. Institute of Polymers.

Kazan National Research Technological University. K. Marx St., 68. Kazan, 420015. Tatarstan Republic.

Russia. Phone: +7 (843) 231-43-88. E-mail: l.musina@yandex.ru

*Supervising author; ⁺Corresponding author

Keywords: pulp and paper materials, sack paper, polylactic acid, unipolar corona discharge.

Abstract

Complex strength properties of sack paper M-70 and sack paper with polylactide coating (polylactide manufactured by Sigma Aldrich) were studied in work. From the photographs of the surface of the sack paper it can be seen that it has a developed fibrous structure with the presence in the composition of various fillers and formations in the form of resin inclusions. The production of paper with a polymer coating was carried out by the trailing blade coating of paper from a solution of polylactide in chloroform. The thickness of the polylactide tape is 1.5-2.0 μm . Coating with a solution method allows the polymer to flow to a greater depth than traditional viscous polyolefins applied to paper from melts. It is shown that applying a coating on the surface of a paper sheet increases the strength parameters (pop strength, wet strength, breaking stress, breaking length, rigidity in tension, resistance to pressure on short distance fracture toughness) by an average of 10% due to the filling of interfiber pores by macromolecules. It is shown that sack paper and sack paper with polylactide coating after processing in a unipolar (negative) corona discharge have low electret characteristics. However, even a low level of surface potential, electric field intensity and effective surface charge density of pulp and paper materials is sufficient to influence their strength characteristics. Comparison of the strength properties between conventional and electret samples of sack paper showed the effectiveness of this hardening method. Processing of pulp and paper materials in a unipolar corona discharge increases the strength properties by 6-15%. The strengthening effect of the electret for the sack paper with polylactide coating is more significant. This is due to the orientation of the segments of the cellulose macromolecules, lignin and polylactide in the electric field and due to the increase in the potential of the double electrical layer on the surface of the fibers under the action of charge carriers injected into the paper during corona treatment.

References

- [1] R.O. Shabiev, A.S. Smolin, Yu.S. Kozhevnikov, I.N. Koverninsky. Paper chemistry: study on action of strengthening and drainage additives. *Chemistry of Plant raw Material*. **2014**. No.5. P.68. (russian)
- [2] D.A. Dul'kin, L.A. Blinova, O.I. Blinushova. Effect of the secondary fiber fineness on cardboard mechanical behavior. *Chemistry of Plant raw Material*. **2007**. No.1. P.85. (russian)
- [3] E.S. Noskova. Effect of hardening additives on fracture pattern of paper and cardboard. *Cellulose. Paper. Cardboard*. **2015**. No.3. P.58. (russian)
- [4] Technology of the pulp and paper production. In 3 volumes. Vol. II. Paper and cardboard production. Part 2. Basic types and properties of the paper, cardboard, fiber and wood boards. *Saint-Petersburg: Politehnika*. **2006**. 499p. (russian)
- [5] Yu.B. Grunin, D.S. Masas, V.I. Talantsev, N.N. Sheveleva, L.Yu. Grunin. Study of cellulose structure and its hydrophilic properties by NMR 1H. *Butlerov Communications*. **2016**. Vol.47. No.8. P.115. DOI: 10.37952/ROI-jbc-01/16-47-8-115
- [6] Yu.B. Grunin, L.Yu. Grunin, V.I. Talantsev, D.S. Masas, E.A. Nikol'skaya. Supramolecular reorganization in biopolymers during the adsorptive process. *Butlerov Communications*. **2014**. Vol.38. No.5. P.23. ROI: jbc-02/14-38-5-23
- [7] Yu.B. Grunin, L.Yu. Grunin, E.A. Nikol'skaya, V.I. Talantsev, D.S. Masas. Supramolecular structure of cellulose. *Butlerov Communications*. **2011**. Vol.24. No.4. P.35. ROI: jbc-02/11-24-4-35
- [8] A.A. Perepelkina, M.F. Galikhanov, L.R. Musina. Effect of thermal and electrophysical treatment on resistance to bursting of the pulp and paper material. *Herald of Kazan Technological University*. **2013**. Vol.16. No.7. P.113. (russian)

- [9] L.R. Musina. Application of corona treatment as a strengthening method for composite corrugated cardboard. *Herald of Kazan Technological University*. **2014**. Vol.17. No.10. P.45. (russian)
- [10] G.A. Gaynanova, M.F. Galikhanov, L.R. Musina, A.I. Nazmieva, V.V. Tyurikova. The effect of the surface treatment of the pouch paper with polylactide coating and corona discharge on its barrier properties. *Herald of Kazan Technological University*. **2016**. Vol.19. No.14. P.119. (russian)