

Effects of slag basicity and B₂O₃ content on the viscosity of CaO-SiO₂-B₂O₃-25%Al₂O₃-8%MgO oxide system

© Anatoly A. Babenco,^{1,2*} Alena G. Upolovnikova,¹⁺ and Artem N. Smetannikov^{1,2}

¹Laboratory of Pyrometallurgy of Non-Ferrous Metals. Institute of Metallurgy of the UB of the RAS. Amundsen St., 101. Ekaterinburg, 620016. Sverdlovsk Region. Russia.

Phone: +7 (343) 232-90-24. E-mail: upol.ru@mail.ru

²Ural Federal University Named after the First President of Russia B.N. Yeltsin. Mira St., 19. Ekaterinburg, 620002. Sverdlovsk Region. Russia.

* Supervising author; + Corresponding author

Keywords: boron containing slags, basicity, viscosity, experimental planning, composition – viscosity diagrams.

Abstract

A simplex-lattice method of experiment planning that allows obtaining mathematical models describing the dependence of the property on composition as a continuous function was used to study the effect of basicity and B₂O₃ content in slag on the viscosity of the CaO-SiO₂-B₂O₃ oxide system containing 25% Al₂O₃ and 8% MgO. Mathematical models describing the relationship between the temperature of a given viscosity and the composition of the oxide system were constructed using experimental data. Then the set of viscosity isolines was obtained by combining the obtained composition-temperature diagrams of a given viscosity by the isothermal section of the composition-viscosity diagram. The generalization of the results presented in the form of composition-property diagrams allowed to quantify the effect of slag basicity and the B₂O₃ content on the viscosity of the resulting oxide system. The viscosity of slag basicity 2.0-2.5, containing 7-10% B₂O₃ does not exceed 4 Ps at a temperature of 1400 °C. The displacement of slags in the region of increased to 3-5 basicities is accompanied by an increase in the viscosity of slags to 12 Ps while the content of B₂O₃ is reduced to 2-6%. An increase in temperature to 1450 °C leads to a significant decrease in slags viscosity, which in the basicity range 2-3, even at a B₂O₃ content of 4%, does not exceed 4 Ps and increases to 6 Ps in basicity 3-5 and a content of B₂O₃ not more than 3%. The slag viscosity in the basicity range 2-5 varies within 2-4 Ps at a B₂O₃ content of 1-4% at a temperature of 1500 °C. It has been established that slags in the basic 2-5 range containing 1-10% B₂O₃ are characterized at constant concentrations of Al₂O₃ (25%) and MgO (8%) with a high liquid mobility, whose viscosity in the temperature range 1450-1500 °C does not exceed 4-6 Ps. Such slags have, as a rule, high refining properties and can be recommended for the formation on the ladle furnace.

References

- [1] S.M. Chumakov, A.M. Lamukhin, S.D. Zinchenko. The concept of production of low-sulfur steels at OAO Severstal, taking into account the technological aspects. Proceedings of the Sixth Congress of Steel-smelters. Moscow: JSC Chermetinform. 2001. P.63-66. (russian)
- [2] S.I. Popel. The theory of metallurgical processes. Moscow: Metallurgiya. 1986. 463p. (russian)
- [3] G.A. Sokolov. Out-of-furnace refining of steel. Moscow: Metallurgiya. 1977. 208p. (russian)
- [4] W. Hongming, Z. Tingwang, Z. Hua. Effect of B₂O₃ on Melting Temperature, Viscosity and Desulfurization Capacity of CaO – based Refining Flux. *ISIJ International*. 2011. Vol. 51. No.5. P.702-708.
- [5] Steel production. Volume 1. Processes of smelting, out-of-furnace processing and continuous casting / Dyudkin D.A., Kisilenko V.V. Moscow: Heat engineer. 2008. 528p. (russian)
- [6] V.I. Kurpas, L.I. Krupman, S.S. Brodsky. Improved technology of out-of-furnace refining of steel. *Sb.nauch.-tekh. statey iz zhurnala «Stal'»*. Moscow: Metallurgiya. 1987. P.61-64. (russian)
- [7] D. Takahashi, M. Kamo, Y. Kurose, H. Nomura. Deep steel desulphurisation technology in ladle furnace at KSC. *Ironmaking and Steelmaking*. 2003. Vol.30. No.2. P.116-119.
- [8] P.K. Iwamasa and R.J. Fruehan. Formation and behaviour of Mn containing oxysulphide inclusions during desulphurisation, deoxidation and alloying. *Metall. Mater. Trans. B*. 28. 1997. P.47.
- [9] P. Yan, X. Guo, S. Huang, J. Dyck, M. Guo, B. Blanpain. Desulphurisation of Stainless Steel by Using CaO-Al₂O₃ Based Slags during Secondary Metallurgy. *ISIJ International*. 2013. Vol.53. No.3. P.459-467.

- [10] Gaye H. and Lehmann J. Modeling and prediction of reactions involving metals, slags and fluxes. VII International Conference on Molten Slags Fluxes and Salts, The South African Institute of Mining and Metallurgy. **2004**, pp. 619–624.
- [11] Hui-xiang Yu, Xin-hua Wang, Mao Wang, Wan-jun Wang Desulfurization ability of refining slag with medium basicity. *Int. J. Miner. Metall. Mater.* **2014**. Vol.21. No.12. P.1160-1166.
- [12] A.A. Akberdin, G.M. Kireeva, I.A. Medvedovskaya. Influence of B_2O_3 on the viscosity of slags of the system $CaO-SiO_2-Al_2O_3$. *Izvestiya AN SSSR. Metall.* **1986**. No.3. P.55-56. (russian)
- [13] H. Wang, G. Li, R. Dai. CAS-OB refining slag modification with B_2O_3-CaO and CaF_2-CaO . *Ironmaking and Steelmaking*. **2007**. Vol.4. No.34. P.350-353.
- [14] A.A. Babenko, S.A. Istomin, E.V. Protopopov, A.V. Sychev, V.V. Ryabov. The viscosity of the slag system $CaO-SiO_2-Al_2O_3-MgO-B_2O_3$. *Izvestiya VUZov. Chernaya Metallurgiya*. **2014**. No.2. P.41-43. (russian)
- [15] V.A. Kim, A.A. Akberdin, I.S. Kulikov. The use of lattices simplex charting-type structure - the viscosity. *Izvestiya VUZov. Chernaya Metallurgiya*. **1980**. No.9. P.167-168. (russian)
- [16] V.A. Kim, E.I. Nikolai, A.A. Akberdin, I.S. Kulikov. *Planirovanie eksperimenta pri issledovanii fiziko himicheskikh svoistv metallurgicheskikh shlakov: Metodicheskoe posobie*. [The planning experiment the study of physical - chemical properties of metallurgical slags: Toolkit]. *Alma-Ata: Nauka*. **1989**. 116p.
- [17] A.G. Upolovnikova, and A.A. Babenco. Thermodynamic modeling of boron recovery from boron-containing slag. *Butlerov Communications*. **2016**. Vol.48. No.10. P.114-118. ROI: jbc-02/16-48-10-114
- [18] A.A. Babenco, L.A. Smirnov, V.I. Zhuchkov, A.V. Sychev, and A.G. Upolovnikova. Using of simplex lattices method for diagramming composition-viscosity of the slag system $CaO-SiO_2-Al_2O_3-MgO-B_2O_3$. *Butlerov Communications*. **2016**. Vol.48. No.11. P.40-44. ROI: jbc-02/16-48-11-40
- [19] Babenko A.A., Zhuchkov V.I., Smirnov L.A. Etc. Research and development of complex manufacturing techniques of low carbon boron steel with low sulfur content. *Stal'*. **2015**. No.11. P.48-50. (russian)
- [20] A.A. Babenko, L.A. Smirnov, V.I. Zhuchkov, E.N. Selivanov. The development of the technology of deep metal desulphurization and microalloying became boron on the UKP under the slags of the $CaO-SiO_2-Al_2O_3-MgO-B_2O_3$ system. *Sbornik trudov XIII mezhdunarodnogo kongressa staleplavil'shchikov: Moscow-Polevskoy*. **2014**. P.174-177. (russian)