

Effect of functional ingredients on the technological properties of rubber mixtures for sealing elements

© Ivan S. Spiridonov, Nikolay F. Ushmarin,
Evgeny N. Egorov, and Nikolay I. Koltsov*⁺

Department of Physical Chemistry and Macromolecular Compounds. Chuvash State University
of I.N. Ulyanov. Moskovsky ave., 15. Cheboksary, 428015. Chuvash Republic. Russia.

Phone: +7 (8352) 45-24-68. E-mail: koltsovni@mail.ru

*Supervising author; ⁺Corresponding author

Keywords: rubber mixture, hydrogenated butadiene-nitrile caoutchoucs, physical and mechanical properties, thermo-aggression resistance, sealing elements.

Abstract

The influence of acrylonitrile content in butadiene-nitrile caoutchoucs, various agents and coagents of vulcanization, antioxidants, technological additives and fibrous fillers on the express control technological properties (plasticity, ring modulus, density) of two model rubber mixtures has been studied in this article. The study has been carried out with the purpose of selecting the basis of rubber mixtures for the manufacturing of thermo-aggressive resistant sealing elements with hardness of 80±5 and 90±5 units. Shor A of packer and anchor equipment for the oil and gas industry. It has been established that rubber mixtures containing BNKS-18AMN caoutchouc with minimum amount of acrylonitrile have satisfactory technological properties. It has been shown that rubber mixtures with hardness of 80±5 and 90±5 units Shor A based on caoutchoucs ZN 35056 and BNKS-18AMN at 90:10 ratio containing Perkadox BC-FF vulcanizing agent and Maleid F coagent, triple combination of amine, phenolic antioxidants and nickel dibutyldithiocarbamate, Zincolet BB-222 processing aid and aramid fiber are characterized by improved technological properties. These rubber mixtures can be recommended as a basis for the manufacturing of thermo-aging resistant sealing elements.

References

- [1] N.I. Kol'tsov, N.F. Ushmarin, A.E. Petrov, N.P. Petrova, N.N. Petrova, S.M. Verkhunov. Investigation of the influence of technological additives on the properties of rubbers based on BNK of a new generation. Part 1. Vuhtazin RV/g-s. *Butlerov Communications*. **2010**. Vol.19. No.2. P.79-86. ROI: jbc-02/10-19-2-79
- [2] N.I. Kol'tsov, N.F. Ushmarin, L.G. Rogozhina, S.A. Issakova, A.V. Yarutkina, A.Yu. Plekhanova, M.V. Kuzmin. Investigation of the influence of technological additives on the properties of rubbers based on BNK of a new generation. Part 2. Elastide, oxanols and factus. *Butlerov Communications*. **2010**. Vol.19. No.3. P.75-82. ROI: jbc-02/10-19-3-75
- [3] N.I. Kol'tsov, N.F. Ushmarin, A.E. Petrov, N.P. Petrova, N.N. Petrova, S.M. Verkhunov. Investigation of the influence of technological additives on the properties of rubbers based on BNK of a new generation. Part 3. Novantox 8 PFDA. *Butlerov Communications*. **2010**. Vol.21. No.9. P.22-28. ROI: jbc-02/10-21-9-22
- [4] N.I. Kol'tsov, N.F. Ushmarin, L.G. Rogozhina, S.A. Issakova, A.V. Yarutkina, A.Yu. Plekhanova, M.V. Kuzmin. Investigation of the influence of technological additives on the properties of rubbers based on BNK of a new generation. Part 4. Powder stabilizers based on Novantox 8 PFDA. *Butlerov Communications*. **2010**. Vol.22. No.10. P.42-50. ROI: jbc-02/10-22-10-42
- [5] N.I. Kol'tsov, N.F. Ushmarin, N.P. Petrova, Yu.V. Vasilieva, A.V. Yarutkina, N.N. Petrova, A.Yu. Plekhanova, M.V. Kuzmin. Investigation of the influence of technological additives on the properties of rubbers based on BNK of a new generation. Part 5. Fire retardants based on combinations of trichloroethyl phosphate. *Butlerov Communications*. **2012**. Vol.29. No.2. P.62-68. ROI: jbc-02/12-29-2-62
- [6] S.I. Sandalov, M.S. Reznikov, N.F. Ushmarin, N.I. Kol'tsov. Development of thermo-aggressive rubber for packer elements. *Bulletin of the Kazan Technol. University*. **2014**. Vol.17. No.9. P.129-132. (russian)
- [7] G.A. Lysova. Hydrogenated butadiene-nitrile rubbers. Properties. Recipe building. Application. Thematic review. Ser. Manufacture of rubber and asbestos technical products. Issue. 6. *Moscow: TsNIITeneftehim*. **1991**. 56p. (russian)

- [8] Y.S. Kovshov, V.V. Moiseev, T.P. Zharkikh, I.P. Zornikov. Hydrogenated butadiene-nitrile rubbers (production, properties and applications). *Caoutchuc and Rubber*. **1990**. No.6. P.28-33. (russian)
- [9] Yu.V. Korovina, U.I. Shcherbina, R.M. Dolinskaya, M.E. Leizeronok. Peroxide curing of hydrogenated butadiene-nitrile rubber. *Caoutchuc and Rubber*. **2007**. No.1. P.4-7. (russian)
- [10] B.Yu. Anisimov, A.S. Dykman, N.S. Imyanitov, S.A. Polyakov. Hydrogenation of butadiene-nitrile rubbers. *Caoutchuc and Rubber*. **2007**. No.2. P.32-38. (russian)
- [11] I.S. Spiridonov, N.F. Ushmarin, S.I. Sandalov, N.I. Koltsov. The effect of hydrogenated butadiene-nitrile caoutchoucs on the properties of rubber for sealing elements. *Butlerov Communications*. **2017**. Vol.50. No.4. P.45-49. DOI: 10.37952/ROI-jbc-01/17-50-4-45
- [12] N.I. Kol'tsov, M.S. Reznikov, N.F. Ushmarin, O.N. Feofanova, S.I. Sandalov. Rubber mixture. Patent 2559833, publ. 08.20.**2015**, the bulletin of inventions No.23. (russian)
- [13] S.I. Sandalov, O.N. Feofanova, M.S. Reznikov, N.F.Ushmarin, D.O. Gnezdilov, N.I. Kol'tsov. Development of thermo-aggressive rubber on the base on butadiene-nitrile caoutchoucs. *Bulletin of the Kazan Technol. University*. **2014**. Vol.17. No.3. P.108-110. (russian)