

Cathode processes in solutions of zinc sulfate in the presence of surface active substances

© Alexander V. Kolesnikov

Chelyabinsk State University. Brothers Kashirins St., 129. Chelyabinsk, 454001. Russia.

Phone: +7 (351) 794-25-12. E-mail: avkzinc-gu@yandex.ru

Keywords: cathodic processes, zinc sulfate, lignosulfonate, flocculants, polarization, dynamic regime, polarization curves.

Abstract

Electrochemical studies of the effect of surfactant additives and a background solution of sodium sulfate on electrode processes involving zinc were carried out. Electrochemical investigations were carried out on a sulfate electrolyte containing 0.005, 0.0125 and 0.025 mol/l $ZnSO_4$ in a background 0.5 mol/l solution of Na_2SO_4 . Individual studies were performed using electrolytes of composition: 0.25 mol/l $ZnSO_4$; 0.25 mol/l $ZnSO_4$ + 18 g/l H_2SO_4 . To the electrochemical cell, the flocculants were dosed in the form of an aqueous solution with a concentration of 2.5 g/l in an amount of 25-50 mg/l. The dosage of flocculants corresponded to their consumption in the hydrometallurgical cycle. Lignosulphonate (LST) was added in an amount of 80 mg/l. The removal of the polarization curves in a dynamic mode was carried out on the potentiostat "Potentiostat P-30 Jcom. Elins Electrochemical Instruments" using a three-electrode cell. The working electrode (cathode) is made of Z0A zinc with the area of 0.35 cm², the auxiliary (anode) is made of platinum plate with the area of 0.20 cm², the reference electrode is silver chloride (Ag/AgCl).

Polarization curves are obtained in dynamic mode at a sweep rate of 100 mV/s in the potential range from -1000 (-1075) to -1250 mV (Ag/AgCl). It is shown that in the presence of a background solution of sodium sulfate, after an initial increase in the cathode current, its decrease occurs at potentials that depend on the ratio of zinc to sodium sulfate in the electrolyte.

When the polarization curves are removed under conditions of intense mixing, the value of the potentials, characterizing the onset of a decrease in the growth of the cathode current density shifts more positively. At a potential of -1200 mV, the cathode current begins to rise again.

The polarization curves obtained in the dynamic mode in the presence of cationic and anionic flocculants and lignosulfonate are consistent with the theory of electrochemical processes. In the presence of additives, the density of the cathode current decreased, which can be related to the blocking of the surface (Loshkarev effect). At the same time, according to the electrochemical theory, the cationic surface active flocculant K6645 flask in the presence of specific adsorption should increase the cathodic polarization of the zinc discharge in connection with the increase of the diffusion potential, which agrees with the experimental data obtained by us. The anionic K4034 flask, as well as the anionic lignosulfonate, in turn, should reduce the cathodic polarization and thereby increase the density of the cathodic current.

References

- [1] A.V. Kolesnikov. Studies of reasons for the effective use of lignosulfonate in the electrolysis of zinc. *Butlerov Communications*. **2014**. Vol.40. No.12. P.110-116. ROI: jbc-02/14-40-12-110
- [2] A.V. Kolesnikov. Investigation of the effect of surfactants with inversion-voltammeterimethod analysis of metals. *Butlerov Communications*. **2016**. Vol.47. No.7. P.93-96. DOI: 10.37952/ROI-jbc-01/16-47-7-93
- [3] A.V. Kolesnikov. Studies of the discharge of the zinc from the background solution of sodium sulfate in the presence of lignosulfonate. *Butlerov Communications*. **2017**. Vol.49. No.1. P.128-135. DOI: 10.37952/ROI-jbc-01/17-49-1-128
- [4] A.V. Kolesnikov. The electroreduction are investigated zinc from the background solution of sodium sulfate in the presence of cationic and anionic flocculants. *Butlerov Communications*. **2017**. Vol.49. No.2. P.130-136. DOI: 10.37952/ROI-jbc-01/17-49-2-130
- [5] A.V. Kolesnikov. Influence of flocculants on the electroreduction of zinc from sulfate solutions. *Bulletin of SSTU "Chemistry and Chemical Technologies"*. **2014**. No.3 (76). P.47-52. (russian)

- [6] O.V. Negvoglod, E.N. Selivanov. The mass transfer during electrochemical oxidation of copper-nickel sulphide alloy granules. *Butlerov Communications*. **2016**. Vol.47. No.8. P.80-86. DOI: 10.37952/ROI-jbc-01/16-47-8-80
- [7] V.V. Pryanichnikova, N.S. Shulaev, N.A. Bykovsky, and R.R. Kadyrov. Electrochemical cleaning of oil-contaminated soil. *Butlerov Communications*. **2016**. Vol.47. No.7. P.47-51. DOI: 10.37952/ROI-jbc-01/16-47-7-47
- [8] A.I. Biryukov, A.P. Tronov, and V.S. Myhametianov. Features corrosion-electrochemical behavior of steels with different chromium content in the highly acidic sulfate media. *Butlerov Communications*. **2016**. Vol.46. No.5. P.61-66. DOI: 10.37952/ROI-jbc-01/16-46-5-61
- [9] N.A. Bykovsky, L.N. Puchkova, and N.N. Fanakova. Electrochemical processing of distiller fluid of the ammonia-soda manufacture. *Butlerov Communications*. **2015**. Vol.43. No.7. P.122-126. DOI: 10.37952/ROI-jbc-01/15-43-7-122
- [10] O.R. Latypov, E.V. Boev, and D.Ye. Bugay. Reducing the rate of corrosion of oil and gas equipment by polarization surface. *Butlerov Communications*. **2015**. Vol.43. No.7. P.127-134. DOI: 10.37952/ROI-jbc-01/15-43-7-127
- [11] A.V. Kolesnikov, K.V. Semenov. Change in the parameters of electrochemical processes in the presence of lignosulfonate. Materials 8 of the international scientific and practical conference "Fundamental and Applied Sciences Today" on May 10-11, **2016**. North Charleston, USA. Vol.1. P.115-118. (russian)
- [12] A.V. Kolesnikov, K.V. Semenov. Electrolysis of zinc from sulfate acidic and neutral solutions in the presence of lignosulfonate. *Actual problems of the humanities and natural sciences*. Iss.1. **2016**. No.4 (87). P.57-60. (russian)
- [13] A.V. Kolesnikov. Cathodic and anodic processes in solutions of zinc sulfate in the presence of surface-active substances. *News of universities "Chemistry and Chemical Technology"*. **2016**. Vol.59. Iss.1. P.53-57. (russian)
- [14] I.V. Minin, N.D. Solovyova. Kinetics of electrically reducing zinc from sulfate electrolyte in the presence of surfactant additives. Herald of the SSTU. *Chemistry and Chemical Technology*. **2013**. No.1(69). P.58-62.
- [15] A.V. Kolesnikov, and K.V. Semenov. Studies of kinetic parameters of the zinc sulfate solution in the presence of an electrochemical system lignosulfonate. *Butlerov Communications*. **2016**. Vol.47. No.7. P.70-73. DOI: 10.37952/ROI-jbc-01/16-47-7-70
- [16] Z. Galyus. Theoretical foundations of electrochemical analysis. *Moscow: Mir*. **1974**. 552p. (russian)
- [17] L.A. Kazanbaev, P.A. Kozlov, V.L. Kubasov, A.V. Kolesnikov. *Hydrometallurgy of zinc (cleaning solutions and electrolysis)*. Moscow, Publishing house "Ore and Metals". **2006**. 176p. (russian)
- [18] A.L. Rotinyan, K.I. Tikhonov, I.A. Shoshina. Theoretical electrochemistry /edited by A.L. Rotinyan. *Leningrad: Chemistry*. **1981**. 424 p. (russian)
- [19] Skorchelletti V.V. Theoretical electrochemistry. Ed. 4th corr. and add. *Leningrad: Chemistry*. **1974**. 568p. (russian)