

## Cation-exchange synthesis of nickel ferrite on an organic matrix

© Elena A. Belaya,<sup>1\*</sup> Maria S. Gryaznova,<sup>1+</sup> Valery V. Victorov,<sup>2</sup>  
Igor N. Kovalev,<sup>1</sup> and Dmitry A. Zherebtsov<sup>3</sup>

<sup>1</sup> Chapter of Solid State Chemistry and Nanoprocesses. Chemical faculty. Chelyabinsk State University  
Brothers Kashirinyh St., 129. Chelyabinsk, 454001. Chelyabinsk region. Russia.

Phone: +7 (922) 735-04-63. E-mail: masha\_gryaznova@mail.ru

<sup>2</sup> Department of Physics and Methods of Teaching Physics. Faculty of Physics and Mathematics.  
South Ural State Humanitarian-Pedagogical University. Lenin St., 69. Chelyabinsk, 454080.

Chelyabinsk Region. Russia. Phone: +7 (919) 357-38-81. E-mail: victorovvv@csru.ru

<sup>3</sup> Chapters of Materials Science and Physical Chemistry of Materials. Faculty of Materials Science  
and Metallurgical Technologies. Polytechnical Institute. South Ural State University. Lenin St., 76.

Chelyabinsk, 454080. Chelyabinsk Region. Russia. Phone: +7 (908) 042-53-07.

E-mail: zherebtsov\_da@yahoo.com

\*Supervising author; <sup>+</sup>Corresponding author

**Keywords:** solid solutions, ferrites, ferrite-nickel spinel, cation-exchange synthesis.

### Abstract

A new method of synthesis of nanosized nickel ferrite with spinel structure is converted, using organic matrix. The role of the organic matrix performs pre-synthesized cation exchange material having a high exchange capacity. In contrast to the known methods of deposition of metal hydroxides by ion exchange materials, a method is proposed for synthesis based on cationic exchange of protons of the ion exchanger for metal ions (iron and nickel) from a solution. The synthesis consists in gradual treatment of cation-exchange material in the H-form, solutions of salts of the respective metals. Cation exchange resin containing metal ions in equimolar proportions is subjected to annealing, resulting in complete combustion of the organic matrix and the formation of the phase ferrite of Nickel. It is established that the sequence of addition of salts does not affect the phase composition of the final product.

The obtained samples were examined by X-ray diffraction, scanning electron microscopy. X-ray phase analysis revealed the formation of spinel structure with space group Fd3m. The average size of crystallites, calculated using the equation of Debye-Scherrer width of the X-ray peaks depends on the annealing temperature and varies from 20 nm at 500 °C to 100nm at 1000 °C. The parameter  $\alpha$  of the cubic spinel lattice made up 8.33 Å. Thermogravimetric studies showed that when heated, the resin treated with salts of metals, there is a flow of sequential processes decomposition of cation, combustion, carbon residue, decomposition of the chloride and finally sulphate of iron and Nickel with formation to 815 °C phases ferrite nickel.

The main advantage of the proposed method is the high degree of homogenization of initial components and a sufficiently low temperature synthesis. It is shown that by using this method it is possible to obtain nanosized ferrite powder of nickel.

### References

- [1] O.V. Galtseva. Solid-phase synthesis of lithium ferrites in a beam of accelerated electrons [Text]: abstract on. dis. for a job. uch. step. Cand. those. Sciences 05.17.11. *Tomsk*. **2009**. 160p. (russian)
- [2] J.G.S. Duque, E.A. Souza, C.T. Meneses, L. Kubota. Magnetic properties of NiFe<sub>2</sub>O<sub>4</sub> nanoparticles produced by a new chemical method. *Physica*. **2007**. Vol.B 398. P.287-290.
- [3] J.Y. Patil, D.Y. Nadargi, J.L. Gurav, I.S. Mulla, S.S. Suryavanshi. Synthesis of glycine combusted NiFe<sub>2</sub>O<sub>4</sub> spinel ferrite: A highly versatile gas sensor. *Materials Letters*. **2014**. Vol.124. P.144-147.
- [4] R. Benrabaa et al. Nickel ferrite spinel as catalyst precursor in the dry reforming of methane: Synthesis, characterization and catalytic properties. *Journal of Natural Gas Chemistry*. **2012**. Vol.21. P.595-604.
- [5] H. Zhao, Z. Zheng, K.W. Wong et al. Fabrication and Electrochemical Performance of Nickel Ferrite Nanoparticles as Anode Material in Lithium Ion Batteries. *Electrochem. Commun*. **2007**. Vol.9. No.10. P.2606-2610.
- [6] M.A. Gabal, S. Kosa, T.S. E.I. Muttairi. Magnetic dilution effect of nano-crystalline NiFe<sub>2</sub>O<sub>4</sub> synthesized via sucrose-assisted combustion route. *Ceramics International*. **2014**. Vol.40. P.675-681.

- [7] S.P. Gubin, Yu.A. Koksharov, G.B. Khomutov, G.Yu. Yurkov. Magnetic nanoparticles: methods of obtaining, structure, properties. *Uspekhi Khimii*. **2005**. Vol.74. P.539-574. (russian)
- [8] M.M. Hessien, Nasser Y. Mostafa, Omar H. Abd-Elkader. Influence of carboxylic acid type on microstructure and magnetic properties of polymeric complex sol-gel driven NiFe<sub>2</sub>O<sub>4</sub>. *Journal of Magnetism and Magnetic Materials*. **2016**. Vol.398. P.109-115.
- [9] R. Sen, P. Jain, R. Patidar, S. Srivastava, R. Rana, N.Gupta, Synthesis and Characterization of Nickel Ferrite (NiFe<sub>2</sub>O<sub>4</sub>) Nanoparticles Prepared by Sol- Gel Method. *Materials Today: Proceedings*. **2015**. Vol.2. P.3750-3757.
- [10] M. Liu, L. Yang, L. Zhang. Functionalization of magnetic hollow porous oval shape NiFe<sub>2</sub>O<sub>4</sub> as a highly selective sorbent for the simultaneous determination of five heavy metals in real samples. *Talanta*. **2016**. P.161. P.288-296.
- [11] C.N. Chinnasamy, A. Narayanasamy, N. Ponpandian et al. Mixed Spinel Structure in Nanocrystalline NiFe<sub>2</sub>O<sub>4</sub>. *Phys. Rev. B*. **2001**. Vol.63. P.184108-184113.
- [12] L. Chen, Y. Yuan, H. Peng, X. Lu, Z. Luo. The production of flower-like NiFe<sub>2</sub>O<sub>4</sub> superstructures consisting of nanosheets via the thermolysis of a heterometallic oxo-centered trinuclear complex *Materials Letters*. **2012**. Vol.67. P.311-314.
- [13] J. Wang, F. Ren, B. Jia, X. Liu. Solvothermal synthesis and characterization of NiFe<sub>2</sub>O<sub>4</sub> nanospheres with adjustable sizes. *Solid State Communications*. **2010**. Vol.150. P.1141-1144.
- [14] Yu.A. Mirgorod, N.A. Borsch, V.M. Fedosyuk, G.Yu. Yurkov. Magnetic properties of nickel ferrite nanoparticles obtained by the flotation-extraction method. *Inorg. Materials*. **2012**. Vol.48. No.12. P.1375-1380. (russian)
- [15] S. Feng, W. Yang, Z. Wang. Synthesis of porous NiFe<sub>2</sub>O<sub>4</sub> microparticles and its catalytic properties for methane combustion. *Materials Science and Engineering B*. **2011**. Vol.176. P.1509-1512.
- [16] M.A.F. Ramalho, L. Gama, S.G. Antonio et al. X-Ray Diffraction and Mossbauer Spectra of Nickel Ferrite. Prepared by Combustion Reaction. *J. Mater. Sci*. **2007**. Vol.42. P.3603-3606.