

The use of the simplex lattice method for constructing the composition-concentration diagram of slag saturation of the CaO-SiO₂-Al₂O₃-MnO-P₂O₅-FeO system with magnesium oxide

© Anatoly A. Babenko,^{1,2*} Maxim V. Ushakov,³
Alena G. Upolovnikova,¹ and Ruslan R. Shartdinov^{1,2+}

¹ Laboratory of Pyrometallurgy of Non-Ferrous Metals. FGBUN Institute of Metallurgy,
Ural Branch of the Russian Academy of Sciences.

Amundsen St., 101. Bratislava, 620016. The Sverdlovsk Region. Russia.

Phone: +7 (343) 232-91-62. E-mail: russianpersen@mail.ru

² Ural Federal University named after the first President of Russia BN. Yeltsin.

Mira St., 19. Yekaterinburg, 620002. The Sverdlovsk Region. Russia.

³ PJSC "STZ" Seversty Pipe Plant. Vershinina St., 7, Polevskoy, 623388.

Sverdlovsk region. E-mail: ushakovmv@stw.ru

*Supervising author; †Corresponding author

Keywords: magnesium oxide, saturation concentration, slag, experiment planning, thermodynamic modeling, composition-property diagrams, local simplex, basicity.

Abstract

One of the tasks of physicochemical analysis is the construction of composition-property diagrams. In this paper, a mathematical modeling of saturation concentration with magnesium oxide of slags of the CaO-SiO₂-Al₂O₃-MnO-P₂O₅-FeO system in a wide range of chemical composition at temperatures of 1550 and 1650 °C was carried out. Variables of the system were restricted: CaO/SiO₂ = 1.5-3; 25-40% FeO; 4% Al₂O₃; 0.3% P₂O₅; 7% MnO. Using the simplex-lattice planning method, adequate mathematical models were obtained for two temperatures of 1550 and 1650 °C in the form of a degree III polynomial, describing the saturation concentration with the magnesium oxide of the slag, depending on its composition. The results of mathematical modeling are presented graphically in the form of composition-concentration saturation diagrams at a fixed temperature. The results of mathematical modeling in combination with the mathematical method of simplex-lattice planning allowed to obtain new data on the dependence of saturation concentration of magnesium oxide in the slag of the CaO-SiO₂-Al₂O₃-MnO-P₂O₅-FeO system in a wide range of chemical composition at temperatures of 1550 and 1650 °C. It can be seen from the diagrams that the influence of the slag basicity on the saturation concentration of MgO and the practical absence of FeO influence on the saturation concentration are clearly traced in the studied region of slag compositions. The maximum concentration of MgO slag saturation is observed in the slag basicity interval 1.5-2.0 and 25-40% FeO concentration, reaching 8.5-10% at 1550 °C and increasing to 9.5-11.5% at 1650°C. An increase in the basicity of the slag to 2.5-3.0 is accompanied by a decrease in the saturation concentration of MgO slag to 6.5-7.5% and to 7.5-8.0% at temperatures of 1550 and 1650°C, respectively. The generalization of the results of modeling and chemical composition of slags of current production made it possible to identify areas (shaded areas) corresponding to the chemical composition of the slag from the melting and oxidizing period, from the analysis of which it follows that during the melting period at 1550 °C, basicities 2.0-2.5 and 20.0-30.0% FeO concentration in slag, the concentration of MgO is sufficient to maintain at a level of 7.5-9.2%, and 8.2-9.5% MgO in the oxidation period at 1650 °C, basicity 2.5-3.0 and 30-40% FeO concentration in slag.

References

- [1] P. Porrachin, D. Onesti, A. Grosso, F. Miani. The role of slag foaming in optimizing of the thermal performance of EAF AC. *Steel*. **2005**. No.4. P.84-86. (russian)
- [2] D. Sanford, V. Garside, K. Shawnville. Increasing of the refractories resistance on DSP by PACIFICSTEEL, New Zealand. *News of Black Metallurgy Abroad*. **2005**. No.1. P.25-26. (russian)
- [3] A.P. Luz, T.A. Avila, P. Bonadia. Foaming of slag in DSP. *News of Black Metallurgy Abroad*. **2011**. No.5. P.24-26. (russian)

- [4] E. Shurman, G. Mann, D. Nole et al. Influence of dissolved MgO on the durability of the dolomite lining of oxygen converters. *Black Metals*. **1985**. No.3. P.33-41. (russian)
- [5] K.Kh. Obb, Yu. Stradtman, M. Raeder. Impact on the dissolution of lime with additives of natural and synthetic fluxes. *Black Metals*. **1978**. No.6. P.834-841. (russian)
- [6] A.A. Babenko, L.Yu. Krivykh, V.V. Levchuk. Effect of magnesium oxide on the refining properties of converter slags. *Bulletin of Higher Educational Institutions. Ferrous Metallurgy*. **2010**. No.4. P.20-23. (russian)
- [7] A.A. Babenko, L.A. Smirnov, L.Yu. Mikhailova. Theoretical bases and technology of melting in oxygen converters and chipboard under magnesian slags. Proceedings of the XIVth International Congress of Steelmakers. *Moscow: Chermetinformaton*. **2016**. P.157-162. (russian)
- [8] A.A. Babenko, L.Yu. Mikhailova, M.V. Ushakov. Thermodynamics and kinetics of deformation of iron-carbon metal under magnesian slags. *Rasplavy*. **2015**. No.3. P.53-60. (russian)
- [9] M.V. Zuev, A.A. Babenko, S.P. Burmasov and others. A set of technological solutions for reducing the energy and material consumption of the process of smelting a steel semi-finished product in modern particle boards. *Metallurgist*. **2014**. No.7. P.45-49. (russian)
- [10] V.A. Kim, A.A. Akberdin, I.S. Kulikov. The use of lattices simplex charting-type structure - the viscosity. *Bulletin of Higher Educational Institutions. Ferrous Metallurgy*. **1980**. No.9. P.167-168. (russian)
- [11] V.A. Kim, E.I. Nikolai, A.A. Akberdin, I.S. Kulikov. The planning experiment the study of physical - chemical properties of metallurgical slags: Toolkit. *Alma-Ata: Nauka*. **1989**. 116p. (russian)
- [12] V.B. Okhotskiy. Models of metallurgical systems. *Dnepropetrovsk: «System technologies»*. **2006**. 287p. (russian)