

Bright memory to the corresponding member of RAS V.A. Zhabreva is dedicated

Preparation of sodium chromophosphate ceramic pigment in system $\text{Cr}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O} - \text{Na}_4\text{P}_2\text{O}_7 \cdot 10\text{H}_2\text{O}$

© Svetlana V. Chuppina,¹ and Maria V. Larina²

¹ Ltd. “NMP Group”. Marshal Blucher Ave., 78. Lit. H. St. Petersburg, 195067. Russia.

Phone: +7 (812) 331-41-51. E-mail: tchoup@mail.ru

² Ltd “Neohim”. Potapova St., 2. Lit.A. St. Petersburg, 195030. Russia.

Phone: +7 (812) 702-12-46. E-mail: mary_larina@mail.ru

*Supervising author; ⁺Corresponding author

Keywords: organosilicate coatings, inorganic pigments, endothermic reaction, phase composition, thermal analysis, SEM-visualization of the morphology of pigment powders, active specific surface, color characteristics.

Abstract

The most economically feasible way to expand the range and improve the properties of organosilicate coatings in the system “polyorganosiloxanes – layered hydrosilicates – pigments” is the use of new inorganic pigments in their composition. In this paper, the synthesis of sodium-chromium phosphate ceramic pigment is considered by mixing equivalent quantities of $\text{Cr}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ and $\text{Na}_4\text{P}_2\text{O}_7 \cdot 10\text{H}_2\text{O}$ crystalline hydrates with subsequent high-temperature treatment. For the products obtained, the data of X-ray phase analysis, complex thermal analysis, active specific surface, SEM-visualization of the morphology of pigment powders are given, color characteristics are described in the CIELAB color coordinate system. In the system under consideration, after heat treatment at 900 °C, a two-phase product is formed, consisting of NaCrP_2O_7 and $\alpha\text{-CrPO}_4$. The synthesized pigment composition contains nanoscale structures. The degree of washing the sediment affects the weight loss when heated in air, the appearance of split, disordered crystal structures and the color shades of the pigment. The synthesized pigment differs from chromium oxide and from the mixture of chromium oxide and titanium dioxide in a lighter tone, the coordinate b^* is closer to the blue region of the spectrum, the a^* coordinate is also shifted more to the blue region, compared to chromium oxide and a mixture of chromium oxide and titanium dioxide, for which the coordinate a^* is shifted to a greater extent in the green region of the spectrum. The use of the crystallization water of the components as a reaction medium, in contrast to dilute aqueous solutions, makes the synthesis of sodium-chromium phosphate ceramic pigment more efficient: the yield of the desired product is significantly increased, the process becomes more manageable, the number of phases in the pigment composition decreases, the synthesis occurs using a smaller amount of water, the quantity of washing wastewater is reduced.

References

- [1] N.P. Kharitonov, V.A. Krotikov, Yu.I. Khudobin. Organosilicate materials, its properties and technology of application. *Leningrad: Nauka*. **1979**. 202p. (russian)
- [2] S.V. Chuppina, V.A. Zhabrev. Organosilicate materials. *St. Petersburg: Liteo*. **2016**. 182p. (russian)
- [3] S.V. Chuppina, V.A. Zhabrev. Organosilicate radiation-resistant deactivatable protective coatings. *Protection of Metals and Physical Chemistry of Surfaces*. **2013**. Vol.49. No.3. P.344-347.
- [4] M.V. Larina, S.V. Chuppina. Adsorption-physical properties of gradient organosilicate coatings. *News of the St. Petersburg State Technical University (Technical University)*. **2012**. No.16 (42). P.86-89. (russian)
- [5] S.V. Chuppina. Physicochemical regularities in the formation and degradation of organosilicate portions in polyorganosiloxane-silicate-oxide systems. *PhD Thesis in Chem. Sciences. St. Petersburg: ISCh RAS*. **2009**. 390p. (russian)
- [6] S.V. Chuppina. Modified polyurethane organosilicate compositions. *Butlerov Communications*. **2006**. Vol.9. No.5. P.38-49. (russian)

- [7] S.V. Chuppina, and V.A. Zhabrev. The effect of glassy additives on the thermal stability of insulating organosilicate coatings. *Butlerov Communications*. **2011**. Vol.28. No.20. P.25-30. ROI: jbc-02/11-28-20-25
- [8] S.V. Chuppina, A.I. Arsiry, and O.N. Lukyanenko. Solvothermal synthesis of barium titanate – a filler for high temperature resistant coatings. *Butlerov Communications*. **2012**. Vol.31. No.9. P.51-58. ROI: jbc-02/12-31-9-51
- [9] S.V. Chuppina, O.V. Kruglova Synthesis of double pyrophosphates of sodium and chromium for pigmentation of organosilicate coatings. *Glass Physics and Chemistry*. **2009**. Vol.35. No.5. P.541-547. (russian)
- [10] S.V. Chuppina, V.A. Zhabrev, M.V. Larina. Preparation of double pyrophosphates in aqueous systems chromium (III) salt – sodium pyrophosphate. *Russian Journal of Inorganic Chemistry*. **2016**. Vol.61. No.11. P.1361-1367. (russian)
- [11] J. Belcouch, L. Monceaux, E. Bordes, P. Courtine. Comparative structural study of mixed metals pyrophosphates. *Material Research Bulletin*. **1995**. Vol.30. No.2. P.149-160.
- [12] D. Gentil. Synthesis, structure and magnetic susceptibility of KCrP_2O_7 , a potential antiferromagnetic magnetoelectric. *Ferroelectrics*. **1997**. Vol.204. No.1. P.35-44.
- [13] M. Sassi, A. Queslati, M. Gargouri. Ionic ac and dc conductivities of NaCrP_2O_7 compound. *Applied Physics. Materials, Science & Processing*. **2015**. No.119. P.763-771.
- [14] A.P. Ivanenko, P.G. Nagornyi, Z.I. Kornienko, R.S. Boiko, I.V. Zatovskii. Determination of indium, chromium, and iron in double alkali phosphate compounds. *Journal of Analytical Chemistry*. **2007**. Vol.62. No.12. P.1167-1169. (russian)
- [15] I.V. Tananaev, A.V. Lavrov, N.N. Chudinova. Study of the mutual determination of chromium nitrate with pyrophosphates of four metals. *Inorganic Materials*. **1968**. Vol.4. No1. P.77-81. (russian)
- [16] Corbridge D.E.C. Phosphorus: Chemistry, Biochemistry and Technology – 6th edition. *Taylor & Francis Group, LLC*. **2013**. 1473p.
- [17] B.Z. Kantor Mineral rasskazyvaet o sebe. *Moscow: Nedra*. **1985**. 165p. (russian)