

## Electrophilic sulfidation in the olygo(arylene sulfide)s synthesis

© Vladimir I. Nedelkin,<sup>1\*</sup> Boris A. Zachernyuk,<sup>1+</sup>  
Lyubov A. Korneeva,<sup>2+</sup> and Ekaterina N. Solovyova<sup>1</sup>

<sup>1</sup> Winemaking and Inorganic and Analytical Chemistry Division. K.G. Razumovsky Moscow State University of Technologies and Management (First Cossack University).  
Zemlyanoy Val St., 73. Moscow, 109004. Russia.

Phone: +7 (499) 236-72-95. E-mail: vinedelkin@mail.ru; zachern@rambler.ru

<sup>2</sup> Chemistry and Electric-Chemical Energetic Division. National Research University "MPEI".

Krasnokazarmennaya St., 14. Moscow, 111250. Russia.

Phone: +7 (495) 362-70-31. E-mail: korneevala@bk.ru

\*Supervising author; <sup>+</sup>Corresponding author

**Keywords:** olygo(arylene sulfide)s, elemental sulfur, aluminum chloride, electrophilic substitution, benzene, thiophenol.

### Abstract

Olygo(arylene sulfide)s (OAS) performance characteristics determine the prospects of their structural material use. This is a chemical resistance at high temperatures, strength, incombustibility, reliability and safety. In contrast to the traditional method for the arylene sulfides preparation by the reaction of halogenated derivatives with Na<sub>2</sub>S (nucleophilic substitution), the amount of waste decreases with electrophilic sulfidation of aromatic hydrocarbons, since the leaving group in the latter case is the hydrogen atom of the aromatic nucleus. In addition, the synthesis of olygo(aryl sulfide)s by the electrophilic sulfidation reaction based on an available raw material the elemental sulfur is reasonable both economically and environmentally. This is due to the low cost of the reagent (1500-3000 rubles/t in Russia) as well as the need to utilize surplus in the Russian Federation sulfur, to be formed in large quantities in sulfur-containing refinery waste and associated nonferrous metallurgy products processing (up to 98% of its total production).

The olygo(arylene sulfide)s were synthesized by the electrophilic sulfidation of the aromatic nuclei in the presence of AlCl<sub>3</sub>; its characteristics were determined by the synthesis conditions. By IR-, NMR-spectroscopy, mass-spectrometry it was showed the tiiliration followed by the phenylene sulfide units intramolecular cyclization.

It was found that the thiophenol tiiliration proceeds due to the sulfur arene homocondensation under the influence of AlCl<sub>3</sub> to form the ring-chain structure oligomers. It may proceed in the absence of the elemental sulfur.

The interaction of aromatic hydrocarbons with elemental sulfur in the presence of a Lewis acid was shown to allow the obtaining products with a wide range of solubility properties (9.8-99.0% in benzene) and softening temperatures (from 80 to 610 °C and higher).

### References

- [1] B.A. Zachernyuk, E.D. Savin, V.I. Nedel'Kin. Recent advances in the chemistry of sulfur-containing poly(arylenes). *Polymer Science. Series C*. **2002**. Vol.44. No.2. P.168-184.
- [2] L.A. Korneeva, V.I. Nedel'kin, B.A. Zachernyuk, and N.V. Kuleshov. Synthesis of Aromatic Polysulfides on the Basis of Sulfur and Naphthalene. *Rus. J. of App. Chem.* **2015**. Vol.88. No12. P.1958-1962.
- [3] V.I. Nedel'Kin, B.A. Zachernyuk, O.B. Andrianova, and others. The oligo(phenylene sulfide)s with terminal thiol groups. *Butlerov Communications*. **2013**. Vol.35. No.7. P.163-166. ROI: jbc-02/13-35-7-163.
- [4] L.A. Korneeva, B.A. Zachernyuk, V.I. Nedel'kin. Synthesis and Properties of Olygo(arylene sulfides) – Products OF Polycondensation Replaced Arenes with Elementary Sulfur. *Natural and Technical Sciences*. **2011**. No2. P.58-60. (russian)
- [5] L.A. Korneeva, B.A. Zachernyuk, V.I. Nedel'kin. Poly(arylene sulfide)s on the dinuclear aromatic hydrocarbons and sulfur basis. *Chemical Industry Today*. **2015**. No.9. P.45-49. (russian)
- [6] L.A. Korneeva, V.I. Nedelkin, B.A. Zachernyuk. The high-temperature transformation of cyclic aromatic sulfides in the presence of Lewis acids. *Butlerov Communications*. **2015**. Vol.42. No.4. P.96-99. DOI: 10.37952/ROI-jbc-01/15-42-4-96

[7] The Chemist and Technologist's new Handbook of. The basic properties of inorganic, organic and organoelement compounds. *St-Pb: World and Family*. **2002**. 1280p. (russian)