

The influence of unipolar nanosecond electropulse effects on the properties of the alloy Cu-1%Cr. The connection properties of the alloy with the duration of melt processing.

© Eduard Y. Goyda,¹ Valery V. Krinsky,² Igor E. Ignatiev,^{1*} Pavel V. Kotenkov,¹ Alexey V. Dolmatov,¹ Vladimir F. Балакирев,¹ and Elena V. Ignateva¹⁺

¹ Institute of Metallurgy. Ural Branch of RAS. Amundsen St., 101. Ekaterinburg, 620016. Russia.
Phone: +7 (343) 232-90-14. E-mail: igx2@mail.ru

² Department of "Electrical Engineering and Renewable Energy" South Ural State University Lenina Ave., 76. Chelyabinsk, 454080. Russia. Phone: +7 (351) 267-90-14. E-mail: kvv@susu.as.ru

*Supervising author; +Corresponding author

Keywords: alloy system, copper-chromium, the melt, the electric pulse effect, electrical resistivity, hardness.

Abstract

The experimentally determined hardness, electrical resistivity, deformation resistance of the alloy Cu-1% Cr produced using irradiation it melts at a temperature of 1300-1350 °C unipolar nanosecond electric pulse effects a frequency of 1000 Hz, a duration of a single signal with 10^{-9} and a power of 10 kW. The dependences of the determined properties of the metal on the duration of electropulse irradiation have been established. A comparison of irradiated and non-irradiated but received in the same thermoremanent conditions, the alloy samples. Seen significant improvement due to electropulse influence as mechanical (hardness increase up to 40%) and electrical (resistivity decrease up to 10%). The deformation resistance of irradiated samples is higher than that of non-irradiated, all the way deformation on a tensile testing machine, and without loss of plasticity. Found that the best time of the electric pulse treatment is 8-10 mins. It is shown that the influence of the melt irradiation on the electrical resistance of the resulting alloy is more significant than its hardness, despite the achieved changes in the values of these characteristics, expressed as a percentage. The method of melt processing are presented in the form of schematic drawings, results of processing in tables, graphs, and mathematical formulas. On the basis of obtained results the conclusion about expediency of application of electric pulse treatment of melts with the aim of improving the properties of the respective alloys.

References

- [1] O.I. Osintsev, V.N. Fedorov. Copper and copper alloy. National and foreign grads. Directory. *Moscow: Mashinostroenie*. **2004**. 336p. (russian)
- [2] S. Patra, K. Mondal. "Densification behavior of mechanically milled Cu-8 at % Cr alloy and its mechanical and electrical properties," *Prog. Nat. Sci.: Mater. Int.* **2014**. Vol.24. P.608-622.
- [3] X. Wei, D. Yu, Z. Sun, Z. Yang, X. Song, and B. Ding. "Effect of Ni addition on the dielectric strength and liquid phase separation of Cu-Cr alloys during the vacuum breakdown," *Vacuum*. **2014**. Vol.109. P.162-165.
- [4] Q. Fang, Z. Kang, Y. Gan, and Y. Long. "Microstructures and mechanical properties of spark plasma sintered Cu-Cr composites prepared by mechanical milling and alloying". *Mater. Des.* **2015**. Vol.88. P.8-15.
- [5] I.E. Ignatiev, A.B. Shubin, and E.V. Ignatieva. Calculation of parameters of vibration mixing metal composites of copper-gallium. *Butlerov Communications*. **2015**. Vol.43. No.7. P.94-99. DOI: 10.37952/ROI-jbc-01/15-43-7-94
- [6] Yuan Yuan, Zhou Li, Zhu Xiao, Ziqian Zhao, Ziqi Yang. Microstructure evolution and properties of Cu-Cr alloy during continuous extrusion process. *Journal of Alloys and Compounds*. **2017**. Vol.703. P.454-460.
- [7] A.B. Shubin, E.V. Ignatieva, and I.E. Ignatiev. Producing of the metallic compositions from the mixes of copper-containing powders and gallium melts: determination of optimum vibration treatment parameters *Butlerov Communications*. **2016**. Vol.45. No.3. P.116-121. DOI: 10.37952/ROI-jbc-01/16-45-3-116

- Full Paper** E.Y. Goyda, V.V. Krinsky, I.E. Ignat'ev, P.V. Kotenkov, A.V. Dolmatov, V.F. Балакирев, and E.V. Ignateva
- [8] Lijun Peng, Haofeng Xie, Guojie Huang & others. The phase transformation and strengthening of a Cu-0.71wt%Cr alloy. *Journal of Alloys and Compounds*. **2017**. Vol.708. P.1095-1102.
- [9] L.E. Bodrova, E.Yu. Goida, E.A. Pastukhov, T.F. Grigor'eva, A.B. Shubin. New ways to harden chrome bronze. *Perspektivnye materialy*. **2014**. No.9. P.66-72. (russian)
- [10] A.S. Rogachev, K.V. Kuskov, N.F. Shkodich, D.O. Moskovskikh, A.O. Orlov, A.A. Usenko, A.V. Karpov, I.D. Kovalev, and A.S. Mukasyan. "Influence of high-energy ball milling on electrical resistance of Cu and Cu/Cr nanocomposite materials produced by spark plasma sintering". *J. Alloys Compd*. **2016**. Vol.688. P.468-474.
- [11] Milan Bizjak, Blaž Karpe, Gregor Jakša, Janez Kovač. Surface precipitation of chromium in rapidly solidified Cu–Cr alloys. *Applied Surface Science*. **2013**. Vol.277. P.83-87.
- [12] Z.M. Zhou, Z.P. Xiao, B.W. Wei, Y. Hu, L.W. Tang, C. Liu. The Numerical Simulation of Rapidly Solidified Cu-Cr Alloys. *Procedia Engineering*. **2012**. Vol.29. P.3944-3948.
- [13] Wen-xiong HE, Yang YU, Er-de WANG, Hong-fei SUN, Hui CHEN. Microstructures and properties of cold drawn and annealed submicron crystalline Cu-5%Cr alloy. *Transactions of Nonferrous Metals Society of China*. **2009**. Vol.19. Iss.1. P.93-98
- [14] I.E. Ignat'ev, E.A. Pastukhov, L.E. Bodrova. Method for alloys obtaining by low frequency processing of their melts. *Saarbrücken: LAP LAMBERT Academic publishing*. **2013**. 170p. (russian)
- [15] W. Wang, C. Li, Y. Wu, P. Zhang. Preparation and properties of Cu-Cr-C self-lubricated composite. *Hot working technol*. **2010**. Vol.22. P.72-74
- [16] M.A. Eremina, S.F. Lomaeva, E.P. Elsukov, L.E. Bodrova, E.Yu. Goida, E.A. Pastuhov. Copper–chromium carbide composites produced by mechanical activation of initial components in the solid and liquid states (**2013**) *Khim. Fiz. Mezosk*. No.15. P.262-269. (russian)
- [17] V.F. Balakirev, V.V. Krymskii, B.A. Kulakov, Ri Hosen. Electropulse nanotechnology. *Ekaterinburg: UB RAN*. **2009**. 14p. (russian)
- [18] V.F. Balakirev, V.V. Krymskii, E.H. Ri, Hosen Ri, N.A. Shaburova. Electropulse treatment of metal melts. *Ekaterinburg: UB RAN*. **2014**. 144p. (russian)
- [19] E.H. Ri, Ri Hosen, S.V. Dorofeev, V.I. Yakimov. Influence of an irradiation of a liquid phase by nanosecond electromagnetic impulses (NEMI) on its structure, crystallization and structure formation processes and properties of casting alloys. *Vladivostok Dal'nauka*. **2008**. 176p. (russian)
- [20] I.E. Ignat'ev, V.V. Krymskii, P.V. Kotenkov, V.F. Balakirev, E.A. Pastukhov, E.V. Ignat'eva. Method of obtaining composite alloys and design for its realization. *Patent RU 2625375 C2*. **2017**. B.20. (russian)
- [21] I.E. Ignat'ev, and I.S. Sipatov. Particular properties of micron size powder particles. *Butlerov Communications*. **2013**. Vol.34. No.5. P.60-66. ROI: jbc-02/13-34-5-60
- [22] I.E. Ignat'ev, E.A. Pastukhov, O.V. Romanova. Mathematical model of metal powder melt impregnation with application of vibration treatment. *Universities' Proceedings. Powder Metallurgy and Functional Coatings*. **2017**. No.1. P.4-10. (russian)
- [23] I.E. Ignat'ev, V.V. Krymskii, P.V. Kotenkov, V.F. Balakirev, E.A. Pastuhov, E.V. Ignat'eva. Joint electro-impulse and low-frequency treatment of metal melt. *Metallurgist*. **2017**. No.4. P.83-86. (russian)
- [24] B.D. Khalezov, O.V. Zayakin, A.S. Gavrilov, and V.I. Zhuchkov Hydro-, pyrometallurgical method of obtaining alloys system Fe-Ni-Cr-Mn-Si. *Butlerov Communications*. **2017**. Vol.52. No.10. P.111-117. DOI: 10.37952/ROI-jbc-01/17-52-10-111
- [25] E.M. Zhilina, S.N. Agafonov, A.S. Russkih, S.V. Zhidovinova, V.P. Chentsov, and S.A. Krasikov. Aluminium interaction with multicomponent oxide system consisting of zirconium, titanium, silicon, iron. *Butlerov Communications*. **2017**. Vol.51. No.7. P.55-60. DOI: 10.37952/ROI-jbc-01/17-51-7-55
- [26] A.B. Shubin, and A.V. Dolmatov. Mechanical and microstructure properties of the metallic composites based on gallium and containing InBi intermetallic compound. *Butlerov Communications*. **2017**. Vol.50. No.6. P.61-65. DOI: 10.37952/ROI-jbc-01/17-50-6-61