

Adsorption of sodium diclofenac on activated carbon, oxide and iron(III) hydroxide

© Irina B. Dmitrieva,* Sergey E. Erdny-Garyaev, Alexander S. Chukhno,[†]
Ekaterina Yu. Pavlova, Maria O. Koryakovskaya, and Anna A. Pyurbeeva

Department of Physical and Colloid Chemistry. St. Petersburg State Chemical-Pharmaceutical Academy.

Professor Popov St., 14. St. Petersburg, 197376. Russia.

Phone: +7 (812) 499-39-00 (4140). E-mail: irina@dmitriyev.ru, alex-chuhno@yandex.ru

*Supervising author; [†]Corresponding author

Keywords: adsorption, sodium diclofenac, activated carbon, iron(III) oxid, spectrophotometry, pH.

Abstract

The adsorption of sodium diclofenac on activated carbon, iron(III) oxide and on freshly precipitated iron(III) hydroxide has been studied. The amount of adsorbed diclofenac is determined from change in concentration of the solutions before adsorption and after adsorption by spectrophotometric method. In this paper, the analytical wavelength for diclofenac sodium is $\lambda = 276$ nm. All measurements of the optical density of the diversifenac solutions is carried out at $\lambda = 276$ in further. It was shown that the adsorption capacity of iron(III) esters is higher than that of activated carbon. Iron oxide is a hydrophilic sorbent, and activated carbon is hydrophobic and naturally iron oxide sorbs the electrolytes better, such as sodium diclofenac. A major disadvantage of iron oxide is its low specific surface area, therefore to remove from the water the same amount of diclofenac by iron oxide because of its low specific surface, it takes ten times more than activated carbon, which obviously isn't beneficial. We proposed using freshly precipitated iron(III) hydroxide as the sorbent considering that activated carbon and iron oxide are expensive sorbents. Iron salts are used in practice as coagulants in the purification of industrial and domestic wastewater. The effect of pH on the sorption of sodium diclofenac on the ash of freshly precipitated iron hydroxide was studied. The following pH values is chosen in the work: 3, 6 and 12 corresponding to the region of high positive, neutral and high negative charges of the iron(III) hydroxide surface. The sol of freshly precipitated iron hydroxide was prepared directly in a solution of diclofenac sodium by the hydrolysis of iron nitrate. The sorbent, obtained in this way with particle sizes of 10-100 nm has a larger specific surface area than activated carbon.

Comparison of sorption isotherms of sodium diclofenac on hydroxide and iron(III) oxide shows a higher sorption capacity of freshly precipitated iron hydroxide, which is due to a very large specific surface area and a large number of active adsorption centers.

References

- [1] S. Judd, C. Judd. The MBR Book: Principles and Applications of Membrane Bioreactors in Water and Wastewater Treatment. *Great Britain*. **2006**. 342p.
- [2] Case Studies GE Water & Process Technologies / pharmaceutical wastewater treatment, Electronic resource. View at :<http://www.gewaterxom/pd^Case%20StudiesCust/Americas/English/CS-PHAR-INDWW-EN-1106-NA%20GE%20Logo.pdf>.
- [3] I.B. Dmitriyeva, K.P. Tikhomolova, A.S. Chukhno, P.P. Prokopovich, V.M. Starov. Investigation of the electrosurface properties of NiO and Fe₂O₃ in azole solutions. *Colloids and Surfaces A: Physicochem. Eng.* **2007**. Vol.241. Iss.1-3. P.45-59.
- [4] I.B.Dmitrieva, A.S. Chukhno, E.Y. Rodionova, R.V. Novichkov. Specific Adsorption of Aspartic Acid on Iron (III) and Nickel (II) Oxides. *Eurasian Chemico-Technological Journal*. **2012**. Vol.14. No.4. P.299.
- [5] A.S. Chukhno, I.B. Dmitrieva, K.P. Tikhomolova, N.V. Voronkova Electro-surface properties of nickel(ii) and iron(iii) oxides in aqueous solutions of 1,2,4-triazole. *Russian Journal of Applied Chemistry*. **2010**. Vol.83. No.7. P.1225-1229. (russian)
- [6] I.B. Dmitrieva, A.S. Chukhno, and E.Yu. Rodionova. The influence of asparagine on electrokinetic and adsorption properties of the iron(III) and nickel(II) oxides. *Butlerov Communications*. **2015**. Vol.41. No.1. P.83-89. ROI: jbc-02/15-41-1-83

- [7] I.B. Dmitrieva, K.P. Tikhomolova, A.S. Chukhno. Specific features of 1,3-diazole adsorption on the surface of NiO and Fe₂O₃. *Russian Journal of Applied Chemistry*. **2005**. Vol.78. No.5. P.727-732. (russian)
- [8] I.B. Dmitrieva, K.P. Tikhomolova, A.S. Chukhno. Adsorption of tetrazole on Ni(II) and Fe(III) oxides. *Russian Journal of Applied Chemistry*. **2006**. Vol.79. No.1. P.50-55. (russian)
- [9] A.S. Chukhno, I.B. Dmitrieva, V.A. Aksinovich, D.S. Silaeva, A.S. Senina, and A.A. Kergentsev. Electrode surface properties of silicon oxide(IV) in aqueous solutions of azoles. *Butlerov Communications*. **2014**. Vol.38. No.5. P.78-83. ROI: jbc-02/14-38-5-78
- [10] A.S. Chukhno, I.B. Dmitriyeva, A.N. Bankina, and E.Yu. Brilliantova. Investigation of interaction of proteins with bioactive nitrogenated heterocyclic compounds at various pH. *Butlerov Communications*. **2013**. Vol.34. No.5. P.91-99. ROI: jbc-02/13-34-5-91
- [11] A.P. Belyaev, V.P. Rubets, and S.A. Belyaeva. Crystallization of cadmium telluride on single crystal substrates cooled with liquid nitrogen. *Butlerov Communications*. **2015**. Vol.41. No.2. P.155-159. ROI: jbc-02/15-41-2-155
- [12] A.P. Belyaev, V.P. Rubets, V.V. Antipov, A.O. Ribnikov, and S.A. Belyaeva. Crystallization of paracetamol of rhombic form. *Butlerov Communications*. **2014**. Vol.37. No.3. P.113-119. ROI: jbc-02/14-37-3-113
- [13] I.B. Dmitriyeva, A.S. Chukhno, and R.V. Novichkov. Interaction of glycine with cations of Fe(III) and Ni(II) in water solutions and on surfaces of their oxides. *Butlerov Communications*. **2013**. Vol.35. No.8. P.133-137. ROI: jbc-02/13-35-8-133
- [14] A.P. Belyaev, A.M. Skvortsov, V.I. Kucuk, I.B. Dmitrieva, L.A. Bakholdina, A.S. Chukhno, V.V. Grishin, N.A. Kupina, E.E. Malakhova. Physical and colloid chemistry. A guide to practical training: a training manual. Under the editorship of prof. A.P. Belyaev. *Moscow: GEOTAR-Media*. **2012**. 320p. (russian)