

Thermodynamic modeling carbothermic reduction of chromium from poor raw materials

© Oleg V. Zayakin,^{*+} Alena G. Upolovnikova, and Vladimir I. Zhuchkov

Institute of Metallurgy of Ural Division of Russian Academy of Science. Amundsen St., 101.

Ekaterinburg, 620016. Sverdlovsk Region. Russia. Phone: +7 (343) 23-29-139. E-mail: zferro@mail.ru

*Supervising author; +Corresponding author

Keywords: metallurgy, chrome ore, ferroalloy, thermodynamic modeling, reduction degree, oxide melt, metal.

Abstract

The main task of metallurgists always has been to increase the transition degree of the leading elements to the melting product. At present, the transition degree of chromium to the alloy varies within wide limits and is 75-92% for different types of chromic ore in obtaining high-carbon ferrochromium. In this regard, the study of carbothermic reduction process of chromium ore materials elements from poor domestic ore raw materials is of considerable interest. Thermodynamic modeling of carbothermic reduction processes for obtaining high-carbon ferrochromium from ores of Saranovskoye deposit and Kempirsai massif was carried out with the approbation of the results obtained under laboratory conditions. Calculations were performed by minimizing thermodynamic potentials using the Chemistry HSC-6.1 software package (Outokumpu). The equilibrium compositions of the interaction products in investigation systems are determined taking into account the most probable chemical reactions determined by the magnitude of the Gibbs energy increment. The results of thermodynamic calculations showed that the degree of chromium recovery from poor and rich ore materials are almost equal and exceed 99% with an increase in temperature > 1450 °C. At a temperature of ≥ 1050 °C, the interaction reaction of chromium oxide with carbon is intensively developed with the formation of Cr_3C_2 carbide, and at reaching 1100 °C – Cr_4C . A high rate of increase in the reduction degree of chromium with an increase in temperature from 1050 to 1450 °C indicates a good reducing ability of the elements of the investigated chromium ore materials. Approbation of the thermodynamic calculations results was carried out high-temperature thermogravimetric method followed by chemical analysis of the smelting products. Experimental studies have shown that the reduction degree of chromium from both samples at a temperature of 1600 °C exceeds 95%. Qualitatively, the nature of the smelting products for the Saranovskoye and Kempirsai ores is monotonous, only the quantitative values are different. In the high temperature region, poor chromium ores are not inferior to rich ores in recovery degree of the basic element, all other things being equal.

References

- [1] L.L. Gal'perin, O.V. Zayakin, Ya.I. Ostrovskij et al. Particularities in production of high-carbon ferrochrome. *Stal'*. **2003**. No.11. P.47-49.
- [2] V.I. Zhuchkov, O.V. Zayakin, L.I. Leontiev et al. Metallurgical characteristics and use of chromic ore in Russia. *Stal'*. **2007**. No.8. P.54. (russian)
- [3] N.A. Vatolin, G.K. Moiseev, B.G. Trusov. Thermodynamic modeling in high-temperature inorganic systems. *Moscow: Metallurgiya*. **1994**. 352p. (russian)
- [4] G.K. Moiseev, G.P. Vyatkin. Thermodynamic modeling in inorganic systems. *Chelyabinsk: SUSU*. **1999**. 256p. (russian)
- [5] G.G. Mikhailov, B.I. Leonovich, Yu.S. Kuznetsov. Thermodynamics of metallurgical processes and systems. *Moscow: MISiS*. **2009**. 520p. (russian)
- [6] H. Lukas, G. Suzana. Computational Thermodynamics: The Calphad Method. *Cambridge University Press*. **2007**. 324p.
- [7] A.A. Akberdin, U. Konurov, A.S. Kim, K.Z. Sarekenov. Diagram of the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3\text{-MgO-Cr}_2\text{O}_3\text{-FeO}$ system and its mathematical model for calculating the phase composition of slags produced by chromium alloys. *Collection of proceedings: Physicochemical and technological issues of metallurgical production in Kazakhstan. Almaty: Iskander*. **2002**. Vol.30.

- [8] A. Roine. Outokumpu HSC Chemistry for Windows. Chemical reactions and Equilibrium software with extensive thermochemical database. *Outokumpu research OY*. **2002**.
- [9] A. Roine. HSC 6.0 Chemistry. Chemical reactions and Equilibrium software with extensive thermochemical database and Flowsheet simulation. *Pori: Outokumpu research Oy*. **2006**. 448p.
- [10] G.G. Richards, D. Dreisinger, A. Peters, J.K. Brimacombe. Mathematical Modeling of Zinc Processes. *Proceedings of the International Symposium on Computer Software in Chemical and Extractive Metallurgy. Canada: Metallurgical Society of the Canadian Institute of Mining and Metallurgy*. **1988**. P.223-252.
- [11] M. Binnewies, E. Milke. Thermochemical data of elements and compounds. *2nd ed. Wiley-VCH. Weinheim*. **2002**.
- [12] H.Y. Sohn. Process Modeling in Non-Ferrous Metallurgy. In: *Treatise on Process Metallurgy: Industrial Processes. Oxford: Elsevier Ltd*. **2014**. P.701-838.
- [13] V.A. Salina, O.V. Zayakin, V.I. Zhuchkov. Study of the silicothermic method for obtaining complex nickel-chromium-containing ferroalloys by thermodynamic modeling. *Science and technology of Kazakhstan*. **2017**. No.4. P.85-90.
- [14] S.N. Tyushnyakov, and E.N. Selivanov. Thermodynamic simulation of phase formation during cooling of zinc-containing cooper-smelting slag. *Butlerov Communications*. **2015**. Vol.43. No.9. P.102-107. DOI: 10.37952/ROI-jbc-01/15-43-9-102
- [15] N.P. Lyakishev, M.I. Gasik. Metallurgy of chromium. *Moscow: ELIZ*. **1999**. 582p. (russian)
- [16] O.V. Zayakin, V.I. Zhuchkov, V.I. Afanasyev. Study of the melting parameters of high-carbon ferrochrome in the ore-reduction furnace. *Elektrometallurgiya*. **2012**. No.8. P.25-27. (russian)
- [17] V.P. Chernobrovin, I.Yu. Pashkeev, G.G. Mikhailov et al. Work baths ferroalloy furnace RKO-16,5, smelting carbon ferrochromium. *Materials of the XII International Conference: Modern Problems of Steel Electrometallurgy. Chelyabinsk: SUSU*. **2004**. P.94-99. (russian)
- [18] O.V. Zayakin, A.G. Upolovnikova, V.I. Zhuchkov. Study of carbothermic reduction of chromium. *Proceedings of the XIV Russian Conference: Structure and properties of metal and slag melts. Yekaterinburg: UrO RAN*. **2015**. P.236-237. (russian)
- [19] O.V. Zayakin, V.I. Zhuchkov, and O.V. Samoilova. Study of process of chromium reduction by carbon. *Butlerov Communications*. **2016**. Vol.45. No.3. P.80-86. DOI: 10.37952/ROI-jbc-01/16-45-3-80
- [20] L.L. Galperin, O.V. Zayakin, V.I. Zhuchkov. Melting of high-carbon ferrochromium from poor chromite ores. *Electrometallurgy*. **2004**. No.7. P.23-28. (russian)
- [21] Ya.I. Ostrovsky, I.A. Veselovsky, V.I. Afanasyev. Development of technology for the production of chromium ferroalloys using poor domestic chromium ore. *Stal'*. **2013**. No.5. P.40-43. (russian)