Subsection: Polymer Chemistry.

Reference Object Identifier – ROI: jbc-02/18-54-6-11

Publication is available for discussion in the framework of the on-line Internet conference "*Butlerov readings*".

http://butlerov.com/readings/
Submitted on June 18, 2018.

## Study of the mechanism of the modification of polyisoprene by the phospholipid concentrate

© Marina E. Tsyganova, <sup>1</sup> Alevtina P. Rakhmatullina, <sup>1</sup> and Vladimir G. Uryadov<sup>2</sup>\*<sup>+</sup>

<sup>1</sup> Department of the Technology of the Synthetic Rubber. <sup>2</sup> Department of Organic Chemistry.

Kazan National Research Technological University.

K. Marx St., 68. Kazan, 420015. The Republic of Tatarstan. Russia.

Phone: +7 (843) 231-43-81. E-mail: vguryadov@mail.ru, uryadov@kstu.ru

\*Supervising author; \*Corresponding author

**Keywords:** synthetic rubber, natural rubber, modification, phospholipid concentrate, phospholipids.

## **Abstract**

A chemical modification of synthetic isoprene rubber with phospholipids was carried out in a solution of toluene at a temperature of 90 °C. It was found that during the interaction of polyisoprene with phospholipid concentrate, the content of double bonds decreases, which indicates the occurrence of chemical reactions. The samples of modified synthetic isoprene rubber were studied by IR spectroscopy,  $^{1}$ H and  $^{13}$ C NMR spectroscopy. In particular, the IR spectroscopic data showed that the bands of absorption of groups characteristic of the phospholipid concentrate are fixed in the spectrum of the modified polyisoprene: hydroxyl and amine (3200-3450 cm<sup>-1</sup>), carbonyl groups in the carboxyl and ester groups (1711 cm<sup>-1</sup> and 1744 cm<sup>-1</sup>, respectively). In addition, the appearance of a new band of 1775 cm<sup>-1</sup> corresponding to the carbonyls in  $\gamma$ -lactones and a decrease in the intensity of the peak characteristic of the vibrations of the groups >C=C< are noted, which indicates the interaction of fragments of phospholipids with macromolecules of polyisoprene. On the basis of an analysis of the change in the position of the bands and their intensities, an assumption is made about the mechanism of modification.

## References

- [1] M.E. Tsyganova, A.P. Rakhmatullina, A.G. Liakumovich, E.E. Potapov, G.S. Stepanova. The study of the composition of phospholipid concentrate polyisoprene modifier. *Fundamental studies*. **2011**. No.12. P.187-193. (russian)
- [2] A.M. Kochnev, A.E. Zaikin, S.S. Galibeev. Physico-chemistry of polymers. *Kazan: Fen.* **2003**. 512p. (russian)
- [3] M.E. Tsyganova, T.M. Bogacheva, N.E. Tsyganov, A.P. Rakhmatullina, A.G. Liakumovich. Evaluation of the compatibility of synthetic polyisoprene with phospholipids. *Bulletin of Kazan Technological University*. **2011**. No.18. P.116-124. (russian)
- [4] N.E. Gelman, Ye.A. Terentyeva, T.M. Shapina Methods of quantitative organic elemental microanalysis. *Moscow: Chemistry.* **1987**. 296p. (russian)
- [5] A.A. Zinoviev. Chemistry of fats. *Moscow: Pishpromizdat.* **1952**. 552p. (russian)
- [6] I. Nifatyev, P. Ivchenko. Practical course of nuclear magnetic resonance spectroscopy. Toolkit. *Moscow: M.V. Lomonosov Moscow State University.* **2006**. 200p. (russian)
- [7] G. Klopman. Reactivity and ways of their reaction: a monograph. *Moscow: Mir.* 1977. 384p. (russian)
- [8] A.S. Onishchenko. Diene synthesis. *Moscow: Because of the Academy of Sciences of the USSR.* **1963**. 613p. (russian)