

Thermodynamic modeling of phase formation during sintering of wolframite concentrate with alkali metal carbonates

© Kirill V. Pikulin,⁺ Lyudmila I. Galkova, and Evgeny N. Selivanov*

Laboratory of Pyrometallurgy of non-ferrous Metals, Institute of metallurgy of the UB of the RAS.

Amundsen St., 101. Yekaterinburg, 620016. Sverdlovsk. Russia.

Tel.: +7 (343) 232-90-24. E-mail: pikulin.imet@gmail.com

*Supervising author; ⁺Corresponding author

Keywords: thermodynamic modeling, wolframite, concentrate, heat, sodium carbonate, potassium carbonate, silicon oxide, equilibrium composition, phase, tungstates.

Abstract

The quality of the wolframite concentrates is deteriorated due to the increased content of copper, molybdenum and iron in the form of sulfates, as well as silica in the form of quartz. Preliminary roasting of raw materials allows to reduce the sulfur content below 1% and convert the metal sulfides to oxides.

Thermodynamic modeling of the sintering of roasted product of low-grade wolframite concentrate (Kalgutinskoe deposit) with alkali metal carbonates was carried out using the software complex HSC Chemistry 6.12. The proportions of the coexisting phases in the temperature range 273-1273 K were quantitatively estimated. The degree of transition of elements to the target products $\text{Na}(\text{K})_2\text{WO}_4$ was established. At the same time, stoichiometric amounts of Na_2CO_3 and K_2CO_3 were used. It was shown that the degree of transition of tungsten from $\text{Fe}_x\text{Mn}_{1-x}\text{WO}_4$ to K_2WO_4 exceeds that for Na_2WO_4 . A complete transition of tungsten to K_2WO_4 was achieved when using K_2CO_3 in an amount of 110% of the stoichiometrically required amount, compared to 170% for Na_2CO_3 . The higher contents of SiO_2 , Al_2O_3 , CuMoO_4 and FeMoO_4 in the raw material reduce the degree of transition of $\text{Fe}_x\text{Mn}_{1-x}\text{WO}_4$ to $\text{Na}(\text{K})_2\text{WO}_4$. It was found that the use of K_2CO_3 instead of Na_2CO_3 leads to a decrease in the likelihood of the development of side reactions of the formation of alkali metal silicates. The decrease in the temperature of the model system leads to a decrease in the proportion of sodium silicates (potassium) in the products of sintering. To reduce the $\text{Na}(\text{K})_2\text{SiO}_3$ content, it is necessary to slowly cool the concentrate sintering product with sodium (potassium) carbonates.

References

- [1] A.N. Zelikman, B.G. Korshunov Metallurgy of rare metals. Moscow: Metallurgy. 1991. 432p. (russian)
- [2] E. Lassner, W.-D. Schubert, E. Lüderitz, H.U. Wolf Tungsten, Tungsten Alloys, and Tungsten Compounds. *Encyclopedia of Industrial chemistry*. 2012. 40p.
- [3] G.N. Kozhevnikov, F.G. Sitdikov, A.G. Vodopyanov. Research and development of technology for processing of wolframite concentrates. Collection of articles "Innovation and Technology Center" Academic "": at the intersection of science and production. Ekaterinburg: UrB RAS. 2010. P.27-39. (russian)
- [4] D.V. Ovtzyn, V.V. Kostyunin, V.N. Potapov, G.N. Kozhevnikov. Method for calcining molybdenite concentrates. *Proceedings of high schools. Non-ferrous metallurgy*. 2009. No.3. P.18-20. (russian)
- [5] N.G. Ageev, S.S. Naboychenko. Metallurgical calculations using the software package HSC Chemistry: a tutorial. Ekaterinburg: UrFU. 2016. 124p. (russian)
- [6] G.G. Mikhailov, B.I. Leonovich, Yu.S. Kuznetsov. Thermodynamics of metallurgical processes and systems. Moscow: National University of Science and Technology «MISIS». 2009. 520p. (russian)
- [7] H.Y. Sohn. Process Modeling in Non-Ferrous Metallurgy. In: Treatise on Process Metallurgy: Industrial Processes (Ed. by S. Seetharaman). Oxford: Elsevier Ltd. 2014. Chapter 2.4. P.701-838.
- [8] N.A. Vatolin, G.K. Moiseev, B.G. Trusov. Thermodynamic modeling in high-temperature inorganic systems. Moscow: Metallurgy. 1994. 352p. (russian)
- [9] G.V. Belov. Thermodynamic modeling: methods, algorithms, programs. Moscow: The scientific world. 2002. 184p. (russian)
- [10] K.V. Pikulin, E.N. Selivanov, and L.I. Galkova. Thermodynamic modeling of phase formation during sintering of wolframite with alkali metal carbonates. *Butlerov Communications*. 2018. Vol.54. No.5. P.152-158. DOI: 10.37952/ROI-jbc-01/18-54-5-152

- [11] F.G. Sitdikov, K.V. Pikulin, L.I. Galkova, E.N. Selivanov, A.G. Vodopyanov. Preparation of calcium tungstate from low-quality concentrates. *Materials of the Intern. scientific-practical. Conference "Abishev Readings-2016. Innovations in complex processing of mineral raw materials "*. Kazakhstan, Almaty. **2016**. P.126-130. (russian)
- [12] G.N. Kozhevnikov, A.G. Vodopyanov, F.G. Sitdikov *Patent of the Russian Federation No. 22993132. 10.02.2007*. Method of processing of wolframite concentrate. (russian)
- [13] F.G. Sitdikov, K.V. Pikulin, L.I. Galkova, E.N. Selivanov, A.G. Vodopyanov Processing of low-grade tungsten concentrates. *Materials of the Intern. scientific-practical. Conference "Rhenium, tungsten, molybdenum - 2016. Scientific research, technological development, industrial application"*. **2016**. P.126-130. (russian)
- [14] K.V. Pikulin, E.N. Selivanov, L.I. Galkova, R.I. Gulyaeva. Features of tungsten extraction from spent catalysts of petroleum organic synthesis. *Non-ferrous metals*. **2017**. No.11. P.31-36. (russian)
- [15] A. Roine. HSC Chemistry for Windows, Chemical Reaction and Equilibrium Software with Extensive Thermochemical Database, Version 5.0. Pori,(Finland). *Outokumpu Research Oy, Information Service. PO Box*. **2002**. T.60.