

Methods of CL-20 product classification

© Svetlana N. Aponyakina,^{*†} Alyona V. Kireeva, George V. Teplov, and Irina I. Zolotukhina

Joint-stock company "Federal Research and Production Center" Altai". Socialisticheskaya St., 1.

Biysk, 659322. Altai. Russia. Phone: +7 (3854) 30-19-05. E-mail: post@frpc.secna.ru

^{*}Supervising author; [†]Corresponding author

Keywords: CL-20, hydroclassification, 2,4,6,8,10,12-hexanitro-2,4,6,8,10,12-hexaazaisowurtzitane, fractional composition.

Abstract

Currently, CL-20 product is considered to be one of the most powerful explosives in the world. The researchers' greatest interest is caused by such unique characteristics of CL-20 as high density and heat of formation exceeding those of the known nitramine class compounds. To ensure the technological and operational characteristics of the blended energy materials, it is necessary to use the CL-20 product of a strictly specified granulometric composition. Therefore, at present, the work to separate the product particles into certain size fractions is being carried out actively. The production of dispersed fractions in a very narrow size range (up to several tens of microns) of the highly disperse CL-20 product is the most complicated.

The paper presents the results of a study of the hydroclassification method on a polydisperse sample of CL-20 and a product with a particle size of less than 50 μm . Based on the analysis of literature data, a laboratory apparatus was designed and installed that is a classifier making flow of the working medium to move in the direction that is opposite one to forces acting onto the mass particles (from the bottom to the top). The working medium was selected, the optimal residence time of the product in the zone of the hydroclassification chamber and the rate of the ascending fluid flow were determined.

The developed method of hydraulic classification made it possible to separate reliably the polydisperse product into four size fractions: 0-50, 50-100, 100-140 and more than 140 μm , as well as to isolate the CL-20 product fraction less than 15 μm . The results obtained are confirmed by microscopic studies and sieve analysis.

References

- [1] A.V. Kireeva, N.V. Rogachevskaya, A.S. Ahnevsky. Getting hexanitrohexaazaisowurtzitane (CL-20, WOW) with a particle size less than 50 microns. *Materials of reports of the V all-Russian scientific and technical conference of young scientists*. **2014**. P.69-71. (russian)
- [2] Y. Bajat, V. Zaynali. Preparation and characterization of nano CL-20 Explosive. *Journal of Energetic materials* **29**. **2011**. P.281-291.
- [3] *Pat. USA* 5712511, Preparation of fine particulate CL-20. Chen M.L. Turner A.D. (USA).
- [4] *Pat. Japan* 11060371, Strayss B., Manning T. (USA).
- [5] *Pat. Japan* 11060372A, Strayss B., Manning T. (C USA).
- [6] J. Xia-bing, G. Xue-yonj, R. Hui, et al. Control of Particle Size and Shape of ϵ -HNIW in Drowning – Out crystallization. *Journal of Chemical Engineering of Japan*. **2012**. Vol.45. No.6. P.380-386.
- [7] Y. Bajat, V. Zaynali. Preparation and characterization of nano CL-20 Explosive. *Journal of Energetic materials* **29**. **2011**. P.281-291.
- [8] *Pat. Korea* 00239893B1, Method for manufacturing micro-sized ϵ -type HNIW crystallization. Kim J.H., Lim Y.J. (Korea)
- [9] B. Yadollah, Z. Vida. Preparation and characterization of nano CL-20 explosive. *Journal of Energetic Materials*. **27**. **08**. **2002**.
- [10] I.V. Melikhov. Crystallization behavior of nanodisperse phases. *Inorganic mat.* **2000**. Vol.36. No.3. P.278-286.
- [11] Y. Bayat, M. Zarandi, P. Khabir-Parsi, A. Salihmi Beni. Statistical Optimization of the Preparation of HNIW Nanoparticles via Oil in Water Microemulsion. *Journal of Chemical Engineering of Japan*. **2012**. Vol.45. No.6. P.380-386.
- [12] A.A. Vasiliev, S.A. Dushenok, A.A. Kotomine, D.V. Dashko. Obtaining and some properties of spheroidal CL-20. *Proceedings of SGTI*. **2013**. Vol.21(47). P.33-38. (russian)

- [13] M.F. Foltz, G.L. Coon, F. Garcia. Nichols III A.L The Thermal Stability of the Polymorphs of Hehanitrohexaazaizowurtzitane, Part I. *Propellants, Explosives, Pyrotechnics*. **1994**. No.19. P.19-25.
- [14] *Pat. Russia* 2452739 Method for producing crystalline 2,4,6,8,10,12-hexanitro-2,4,6,8,10,12-hexaazatetracyclo[5, 5, 0, 03,11, 05,9]dodecane with specified polymorphic composition (variants)/ Yu. T. Lapina, A. A. Lobanova, A. Savitsky, etc. (Russia 08.08.2012).
- [15] G.V. Teplov, N.V. Bychin, I.I. Zolotukhina, and V.N. Popok. Synthesis of ultrafine CL-20 crystals by means of destruction of co-crystals on its base with some polar solvents. *Butlerov Communications*. **2017**. Vol.49. No.3.P.101-107. ROI: jbc-02/17-49-3-101
- [16] S.N. Aponyakina, Yu.T. Lapina, I.I. Zolotychina. Crystallization of fine product CL-20. *Butlerov Communications*. **2016**. Vol.48. No.12. P.143-149. ROI: jbc-02/16-48-12-143
- [17] A.V. Kireeva, S.N. Aponyakina, A.S. Ohnevsky, N.V. Rogachevskaya. Ways to improve the morphological and granulometric characteristics hexanitrohexaazaisowurtzitane. *Reports of the IV all-Russian scientific-practical conference of young scientists and specialists*. **2015**. P.216-220. (russian)
- [18] M.D. Barskii, V.I. Revnivitsev, Yu.V. Sokolkin. Gravitational classification of granular materials. *Moscow: Nedra*. **1974**. P.232. (russian)
- [19] S.N. Aponyakina, I.I. Zolotukhina, and A.V. Kireeva. Modification of hexanitrohexaazaisowurtzitane crystals by the method of hydromechanical rolling. *Butlerov Communications*. **2018**. Vol.54. No.5. P.50-53. ROI: jbc-02/18-54-5-50