

Formation of microcrystalline corundum in hydrothermal conditions

© Alexander V. Tolchev⁺ and Artem P. Tronov*

Department of Chemical Technology and Computational Chemistry. Chelyabinsk State University.

Br. Kashirinuh St., 129. Chelyabinsk, 454001. Chelyabinsk Region. Russia.

Phone: +7 (351) 799-70-64. E-mail: arteq_tron@mail.ru

*Supervising author; ⁺Corresponding author

Keywords: solutions of Al(III) and Fe(II) salts, coprecipitation, hydrothermal processing, the electronic scanning microscopy, radiography, lattice parameter, nucleus new phase.

Abstract

By methods of X-ray analysis and electronic raster microscopy were studied features phase- and grainformations in the «oxide of aluminum(III) – oxide of iron(III)» system in hydrothermal conditions. For this purpose samples was synthesized by joint sedimentation by the alkaline agent from water solutions of salts of aluminum(III) and iron(II) with the subsequent hydrothermal processing of the received rainfall at 450 °C within 4 hours. Al₂O₃:Fe₂O₃ ratio in draft was 20:1. Besides, sedimentation of Al(III) salts was carried out without addition of salts of iron.

It is shown that joint sedimentation of solutions of Al(III) and Fe(II) salts and the subsequent hydrothermal processing of the received deposit promotes formation of a monodisperse oxide of aluminum of α -modification (corundum), possessing a hexagonal facet and the average size ~ 1 micron in the diameter and 150-200 nanometers thick.

Equality of sizes of parameters of an elementary cell in corundum samples with an additive of compounds of iron and without them has allowed to draw a conclusion that in these hydrothermal conditions solid Fe₂O₃ solution in the structure of α -Al₂O₃ is n't formed. At the same time, according to numerous literary data, at heat treatment of coprecipitation samples on air, at temperatures over 1100 °C formation of corundum is followed by formation of solid solution as indicated by changes of parameters of an elementary crystal cell of the structure of corundum.

Was made the assumption that owing to isodegree of the structure of α -oxide of iron(III) with corundum, the crystal which is formed at lower temperatures α -Fe₂O₃ act as germs for thermodynamic steadier phase α -Al₂O₃ what leads to decrease in the average size of crystals of the phase α -Al₂O₃, and increase in degree of monodispersion.

Without the addition of compounds of iron, in similar conditions, the polydisperse corundum consisting of tablet crystals, from 5 to 20 microns in the diameter and up to 5 microns thick, tending to a hexagonal facet is formed.

References

- [1] Y.D. Tretyakov. New generations of ceramics. *Vestn. AN SSSR*. **1994**. No.2. P.98-111. (russian)
- [2] E.S. Lukin, N.A. Makarov, I.V. Dodonova, S.V. Tarasova. New ceramic materials based on aluminum oxide. *Refractories and technical ceramics*. **2001**. No.7. P.2-10. (russian)
- [3] A.P. Garshin, V.M. Gropyanov, Y.V. Lagunov. Abrasive materials. *Leningrad: Engineering*. **1983**. 231p. (russian)
- [4] A.V. Tolchev, D.G. Kleshev, V.I. Lopushan. The effect of mechanochemical activation and the addition of α -Fe₂O₃ on the formation of corundum during thermal transformations of γ -Al(OH)₃. *Journal of Applied Chemistry*. **2002**. Vol.75. No.9. P.1417-1421. (russian)
- [5] A.V. Tolchev, D.G. Kleshev, V.I. Lopushan. Effect of dispersion of gibbsite on the kinetics of its transformations. *Inorganic Materials*. **2001**. Vol.37. No.12. P.1493-1496. (russian)
- [6] Knunjac I.L. Chemical Encyclopedia. In 5 tons. *Moscow: Sov. Encycl*. **1983**. Vol.1. 623p. (russian)
- [7] Cards. Database of powder diffractometry, version 3.0. (russian)