

Thematical course: Use of biopulping for pretreatment of wood in bioethanol production. Part 2.

Effect of biopulping on reactivity of wood substrates during fermentative hydrolysis

© Andrey G. Dontsov⁺, and Irina E. Sharapova*

Biochemistry and biotechnology laboratory. Biology Institute of Komi Scientific Center of Ural Department of the Russian Academy of Sciences. Kommunisticheskaya St., 28. Syktyvkar, 167982. Komi Republic. Russia.
Phone: +7 (904) 100-19-55. E-mail: scharapova@ib.komisc.ru

*Supervising author; ⁺Corresponding author

Keywords: biopulping, macromycetes, micromycetes, lignocellulosic materials, solid state fermentation, reactivity.

Abstract

The research focused on the study of strains of basidiomycetes and micromycetes in terms of prospects of their use for pretreatment (biopulping) of different wood substrates along with physical and chemical treatment methods. We have assessed the growth of selected strains of fungi during solid state fermentation on aspen sawdust within 7, 14 and 23 days with and without steam explosion treatment (T = 187-240 °C), as well as on softwood sawdust with and without alkaline hydrolysis treatment. Untreated aspen sawdust autohydrolysed at T = 187 °C was found to be the most adapted substrate for biopulping of lignocellulosic materials for strains of micromycetes (*Penicillium sp.*, *Trichoderma lignorum* (F-98), *Beauveria bassiana* (F-145)) and basidiomycetes (*Panus tigrinus* (F-8/18), and oyster mushroom (*Pleurotus eryngii*)). Reactivity of different softwood and hardwood substrates subjected to biopulping using strains of fungi during solid phase fermentation within 7, 14 and 23 days, was assessed. Strain of *Trichoderma lignorum* was found to be the most promising for pretreatment as it demonstrates increase in reactivity by day 7 of treatment. It was found that combination of biopulping and physical and chemical treatment of wood pulp, including poorly hydrolysable softwood, allows to increase reactivity of substrates. It was established that reactivity of wood substrates can be increased during solid state fermentation using mixed culture based on strains of micromycetes *Beauveria bassiana* and *Penicillium sp.*

It was demonstrated that maximum positive effect of biopulping on reactivity of lignocellulosic substrates caused by the complex of lignocellulolytic enzymes synthesized by fungi, was during solid phase fermentation of hardwood samples. For the most poorly hydrolysable softwood pulp, it looks promising to combine alkaline pretreatment and biopulping with basidiomycetes.

References

- [1] S. Behera, R. Arora, N. Nandhagopal, S. Kumar. Importance of chemical pretreatment for bioconversion of lignocellulosic biomass. *Renew Sustain Energy Rev.* **2014**. Vol.36. No.8. P. 91-106.
- [2] J.S. Tolan. Iogen's process for producing ethanol from cellulosic biomass. *Clean Technologies and Environmental Policy.* **2002**. Vol.3. P. 339-345.
- [3] R.R. Singhanian, R.K. Sukumaran, A. Pandey. Improved cellulase production by *Trichoderma reesei* RUT C30 under SSF through process optimization. *Appl Biochem Biotechnol.* **2007**. Vol.142. No.1. P.60-70.
- [4] N.K. Harner, X. Wen, P.K. Bajwa, et al. Genetic improvement of native xylose-fermenting yeasts for ethanol production. *J Ind Microbiol Biotechnol.* **2015**. Vol. No.42. P.1-20.
- [5] Ú. Fillat et al. Potential of the new endophytic fungus *Hormonema sp.* CECT 13092 for improving processes in lignocellulosic biorefineries: biofuel production and cellulosic pulp manufacture. *Journal of Chemical Technology and Biotechnology.* **2017**. Vol.92. No.5. P.997-1005.
- [6] R.L. Giles et al. Two-stage fungal biopulping for improved enzymatic hydrolysis of wood. *Bioresource technology.* **2011**. Vol.102. No.17. P.8011-8016.
- [7] Baba Y. et al. Pretreatment of Japanese cedar wood by white rot fungi and ethanolysis for bioethanol production. *Biomass and bioenergy.* **2011**. Vol.35. No.1. P.320-324.

- [8] D.A. Satton, A.V. Fotergill, M.G. Rinaldi. The identifier of pathogenic and conditionally pathogenic fungi. Translated from English. *Moscow: Mir*. **2001**. 486p. (russian)
- [9] M.A. Litvinov. The identifier of microscopic soil fungi. *Moscow: Nauka*. **1967**. 312p. (russian)
- [10] N.B. Gradova et al. The laboratory practicum on general microbiology. *Moscow: D.I. Mendeleev University of Chemical Technology*. **1999**. 130p. (russian)
- [11] The methods of experimental mycology. Ed. V.I. Bilai. *Kiev: Naukova dumka*. **1982**. 552p.
- [12] A.V. Obolenskaya et al. Practical tasks on timber and cellulose chemistry. *Moscow: Lesnaya promyshlennost*. **1965**. 320p. (russian)
- [13] A.G. Dontsov, A.P. Karmanov, L.S. Kocheva, A.V. Rudkovsky, S.A. Kuznetsova, V.V. Volodin. The effects of ultrasound cavitation on the reactivity of lingo-cellulose substrates after plant biomass bioconversion. *Butlerov Communications*. **2014**. Vol.39. No.9. P.52-57. ROI: jbc-02/14-39-9-52
- [14] N. Nelson. A photometric adaptation of the Somogyi method for the determination of glucose. *J. Biol. Chem.* **1944**. Vol.163. P. 375-380.
- [15] M. Somogyi. A new reagent for the determination of sugars. *J. Biol. Chem.* **1945**. Vol.160. P.61-68.
- [16] A.G. Dontsov, D.V. Tarabukin, E.V. Vanchikova. Optimization of protein determination in enzyme solutions by the Loury method. *Factory Laboratory. Diagnostics of Materials*. **2009**. Vol.75. No.2. P.18-20. (russian)
- [17] I.E. Sharapova. Use of biopulping for pretreatment of wood in bioethanol production. Part 1. Sampling of strains of basidiomycetes and micromycetes for biopulping of wood substrates. *Butlerov Communications*. **2018**. Vol.56. No.11. P.140-145. ROI: jbc-01/18-56-11-140