

Kinetics of calcium hydroxide interaction with NaCl–H₂SO₄–H₂O solutions

© Igor N. Tanutrov,* Simon O. Potapov, and Marina N. Sviridova[†]

Institute of Metallurgy of Ural Branch of Russian Academy of Sciences.

Amundsen St., 101. Ekaterinburg, 620016. Sverdlovsk Region. Russia.

Phone: +7 (904) 380-56-57. E-mail: intan38@live.ru

*Supervising author; [†]Corresponding author

Keywords: calcium hydroxide, aqueous solution, sodium chloride, sulfuric acid, reaction, kinetics, thermography.

Abstract

The kinetics of the interaction of calcium hydroxide powder with NaCl–H₂SO₄–H₂O solutions was studied using a thermographic method modified by us in relation to the task. A device was used that provides a record of the temperature in the reactor with an accuracy of 0.1 °C with a frequency of 5 sec and a record of the signal to the computer in the form of a graph in the coordinates "temperature – time", as well as in a tabular form. The composition of the solutions was changed in the range of total (NaCl + H₂SO₄) concentrations from 0.1 to 2.0 mol/l and, changing within the interval, the H₂SO₄ concentration from 0 to 2 mol/l. Of the two possible reactions, the reaction with formation of calcium sulphate is more thermodynamically more preferable than with the formation of calcium chloride.

With an initial solution volume of 100 ml, the amount of calcium oxide responded to the formation of sulfate, the amount of oxide being introduced with an excess of 20 mol %. Experiments were performed at the initial temperatures of the solution in the reactor 23.8, 34.3, 45.1 and 51.0 °C. Subsequent analyses of the composition of the solution and measurement data used for the compilation of material and heat balances. On the basis of heat balance you performed the determination of the kinetic equation by analyzing the curves of the "temperature-time". It is found that the increasing part of the curve in the region from the initial to the maximum temperature is approximated by a polynomial of degree 3, and the falling part of the curve of the graph is linear. The dependence of the reaction rate (1) on the solution composition and temperature was determined by mathematical processing of both parts of the graph. It is also determined that the type of speed dependence on the degree of transformation does not meet the known kinetic models of heterogeneous processes. It is found that due to the exothermicity of the process its kinetics is controlled by convective heat exchange. On the basis of the research kinetic parameters are established: the speed constant equal to 6.667 mol/ s, the order of H₂SO₄ concentration in the solution equal to 0.311, the activation energy equal to 50.70 kJ/mol and the dependence of the speed on the degree of transformation in the form of an equation that determines the deviation from the kinetic model of the contracting nucleus.

References

- [1] V.M. Andreev, A.S. Kuznetsov, G.I. Petrov, L.N. Sigina. Production of germanium. *Moscow: Metallurgy*. **1969**. 96p. (russian)
- [2] V.F. Borbat, Yu.L. Mikhailov, L.N. Adeeva, O.A. Golovanova, T.N. Filatova. Study of the possibility of enrichment of fly ash from CHP for rare and non-ferrous metals for their subsequent extraction. *Chemistry and chemical technology*. **1999**. Vol.42. Iss.5. P.86-90. (russian)
- [3] S.O. Potapov, M.N. Sviridova, I.N. Tanutrov, D.A. Toloknov. The physics-chemical properties of fly-ash from the burning of Ekibastuz coals. *Butlerov Communications*. **2016**. Vol.45. No.3. P.36-39. DOI: 10.37952/ROI-jbc-01/16-45-3-36
- [4] S.O. Potapov, M.N. Sviridova, I.N. Tanutrov. The behavior of gallium and aluminum during sulfuric acid processing of fly-ash from reftinskaya hydroelectric power plant. *Butlerov Communications*. **2016**. Vol.45. No.3. P.40-43. DOI: 10.37952/ROI-jbc-01/16-45-3-40
- [5] I.N. Tanutrov, M.N. Sviridova. Thermodynamics of solutions NaCl–H₂SO₄–H₂O. *Butlerov Communications*. **2016**. Vol.51. No.7. P.25-30. DOI: 10.37952/ROI-jbc-01/16-51-7-25
- [6] N.G. Ageev, S.S. Naboychenko. Metallurgical calculations using the hscchemistry: studies application package benefit. *Yekaterinburg: Ural publishing House. UNTA*. **2016**. 124p. (russian)

- [7] A.N. Dyachenko, V.V. Shagalov. Chemical kinetics of heterogeneous processes. *Tomsk: publishing House of Tomsk Polytechnic University*. **2014**. 102p. (russian)
- [8] A.R. Akhmedgoraeva, A.A. Biryukov, L.Yu. Zakirova, M.E. Zakirov, and A.R. Efimova. Study of the technological additive influence on the thermal properties of dynamic thermoplastic elastomer by differential scanning calorimetry and thermal gravimetric analysis. *Butlerov Communications*. **2017**. Vol.50. No.4. P.85-89. DOI: 10.37952/ROI-jbc-01/17-50-4-85
- [9] I.V. Tsyganova, and V.P. Balykin. Thermogravimetric analysis of ammonium-iron (II) sulphate. *Butlerov Communications*. **2018**. Vol.55. No.8. P.102-108. DOI: 10.37952/ROI-jbc-01/18-55-8-102
- [10] K.V. Bryankin, N.P. Utrobin, V.S. Orekhov, T.P. Dyachkova. General chemical technology. *Tambov: Publishing house Tamb. state tech. UNTA*. **2006**. Part 2. 172p. (russian)
- [11] F.F. Tsvetkov, B.A. Grigoriev. Heat and mass transfer: a textbook for universities. 2nd ed. *Moscow: Publishing house MEI*. **2005**. 550p. (russian)