Full Paper

Reference Object Identifier - ROI: jbc-02/18-56-12-10 Publication is available for discussion in the framework of the on-line Internet conference "Butlerov readings". http://butlerov.com/readings/ Submitted on November 12, 2018.

The nature of supramolecular structure changes and hydrophilic properties of cellulose in adsorption-desorption processes

© Yury B. Grunin,¹*⁺ Maria S. Ivanova,¹ Tatiana Y. Grunina,² Gocha Sh. Gogelashvili,¹ and Darva S. Masas¹

¹ Department of Physics. Volga State University of Technology. Lenin Sq., 3. Yoshkar-Ola, 424000. Mari El Republic. Russia. Phone: +7 (8362) 68-68-04. *E-mail: GruninYB*@*volgatech.net*

² Department of Biophysics. Lomonosov Moscow State University. Leninskie Gory, 3, Bld.12. Moscow, 119991. Russia. Phone: +7 (495) 939-27-76. E-mail: info@mail.bio.msu.ru

*Supervising author; ⁺Corresponding author

Keywords: cellulose, NMR relaxation, water adsorption, degree of crystallinity, surface area.

Abstract

A modernized scheme of the structural organization of cellulose, taking into account the peculiarities of its capillary-porous system, is proposed. The paper describes the process of adsorption of water molecules on the hydrophilic walls of porous formations between the structural elements of cellulose. Within the framework of the Brunauer-Emmett-Teller theory, the nature of the interaction of the components of the cellulose-water system is studied using isotherms of adsorption and desorption of water vapor on cellulose. It is established that the process of cellulose moistening is accompanied by an increase in the specific surface and a decrease in the degree of its crystallinity. Within the framework of the modern concepts of the physicochemical chemistry of surface phenomena, the lateral dimensions of the slit-like pores, characteristic of cellulose and its derivatives, are calculated, which are filled with water at the corresponding values of the relative vapor pressures of the adsorbent. In the framework of the theory of surface phenomena, it is postulated that when capillary condensation occurs in narrow pores, a concave fluid meniscus is formed, leading to a decrease in Laplace pressure, which causes enhanced adsorptive diffusion in the area under consideration and, as a result, the transition of unsaturated steam to saturated with the formation of a dew point. It is shown that the adsorption-desorption hysteresis observed in the entire range of relative vapor pressures of the adsorptive, to a large extent, is associated with the appearance of an additional capillary-porous system due to the wedging pressure from the condensing water molecules. This is confirmed by the fact that the calculated values of the monolayer capacity and specific surface area for the desorption isotherm significantly exceed the corresponding values for the adsorption branch. It is found that the proportion of the specific surface belonging to the pore walls of cellulose, in relation to the total specific surface, both during adsorption and during desorption, does not exceed 70%.

References

- [1] Z.A. Rogovin Cellulose Chemistry. *Moscow*. **1972**. 520p. (russian)
- [2] A.D. French Glucose, not cellobiose, is the repeating unit of cellulose and why that is important. Cellulose. 2017. Vol.24. Iss.11. P.4605-4609.
- [3] N. Baiklz, L. Segal. Cellulose and cellulose derivatives: vol. 1-2. Edited by Z.A. Rogovin. *Moscow.* 1974. Vol.1. 500p. (russian)
- [4] Y.B. Grunin [et al.] Microstructure of cellulose: NMR relaxation study. *Polymer Science. Series A.* 2012. Vol.54. No.3. P.201-208.
- [5] Y.B. Grunin [et al.] Features of the structural organization and sorption properties of cellulose. *Polymer* Science Series A. 2015. Vol.57. Iss.1. P.43-51.
- [6] V.P. Nikolaev, A.A. Ageev, Y.G. Frolov. Isopiestic method of analysis. Works MKhTI them. D.I. Mendeleev. 1978. Iss. 101. 84-101p. (russian)
- [7] NMR analyzer «Spin Track». URL: http://www.nmr-design.com.
- [8] V.I. Chizhik. Nuclear magnetic relaxation. St. Petersburg: SPbSU. 2004. 385p. (russian)

- [9] [Y.B. Grunin [et al.] Supramolecular reorganizations in cellulose during hydration. *Biophysics.* 2015. Vol.60. No.1. P.43-52.
- [10] S.J. Gregg, K.S.W. Sing Adsorption, Surface area and Porosity. *Moscow.* **1984**. 2ed. 306p. (russian)
- [11] Y.B. Grunin [et al.] Features of the sorption of water vapor and nitrogen on cellulose. *Russian Journal* of Physical Chemistry A. 2013. Vol.87. No.1. P.100-103.
- [12] Y.B. Grunin Analysis of the cellulose-water system by modified methods of proton magnetic resonance: Doctor's thesis. Riga. 1989. 452p.
- [13] R.M. Brown Cellulose structure and biosynthesis: What is in store for the 21-st century? Journal of Polymer Science. Part A: Polymer Chemistry. 2004. Vol.42. P.487-495.
- [14] Y. Nishiyama Structure and properties of the cellulose microfibril. *Journal of Wood Science*. 2009. Vol.55. P.241-249.
- [15] Q. Li, S. Renneckar Supramolecular structure characterization of molecularly thin cellulose I nanoparticles. Biomacromolecules. 2011. Vol.12. No.3. P.650-659.
- [16] Y.B. Grunin [et al.] Features of Dispersing of Crystalline Cellulose at Its Moistening. *Chemical fibers*. 2017. No.5. P.31-36.
- [17] Y.I. Gerasimov Physical chemistry course: vol. 1-2. *Moscow*. **1964**. Vol.1. 624p. (russian)
- [18] M.M. Dubinin New in the Field of Adsorption of Vapors by Microporous Adsorbents. *Journal of* Physical Chemistry. 1987. No.5. P.1301-1305.