

Experimental studies of periclase-carbon refractories solubility in the slags of the system $\text{CaO-SiO}_2\text{-B}_2\text{O}_3\text{-Al}_2\text{O}_3$

© Anatoly A. Babenco,* Leonid A. Smirnov,

Alena G. Upolovnikova,⁺ and Artem N. Smetannikov

Laboratory of Pyrometallurgy of Non-Ferrous Metals. FSBIS Institute of Metallurgy of the UB of the RAS. Amundsen St., 101. Ekaterinburg, 620016. Sverdlovsk Region. Russia.

Phone: +7 (343) 232-91-62. E-mail: upol.ru@mail.ru

*Supervising author; ⁺Corresponding author

Keywords: experimental design, local simplex, periclase-carbon refractory, solubility, synthetic slag, basicity, boron oxide, composition – solubility diagram.

Abstract

The study of the effect of boron oxide and the basicity of the $\text{CaO-SiO}_2\text{-B}_2\text{O}_3$ system slags containing 15% Al_2O_3 on the solubility of periclase-carbon refractories was carried out using a simplex – lattice method of experiment planning, which allows to construct mathematical models describing the dependence of the property being studied on the composition as a continuous function. Synthetic slags, corresponding in composition to the vertices of the simplex under study, were smelted in graphite crucibles from previously calcined oxides of analytical grade. Experimental compositions of slags corresponding to the remaining points of the local simplex plan were obtained by counter-mixing slag to the tops of the simplex. Using experimental data, we constructed mathematical models that adequately describe the effect of slag composition on wear degree of refractory sample. The graphic image of mathematical modeling results is represented by the composition diagram - the solubility of the refractory sample. An analysis of the experimental data in the diagram made it possible to obtain new data and quantify the effect of boron oxide and the basicity of the $\text{CaO-SiO}_2\text{-B}_2\text{O}_3$ system slags, containing 15% Al_2O_3 on the solubility of periclase-carbon refractories. It is shown that slags formed in the basicity 2-3 range, containing 4-6% B_2O_3 , are characterized by a rather high aggressive effect on periclase-carbon refractory. The wear degree of the refractory sample varies from 25 to 40%. A decrease in the B_2O_3 content in the slag to 14% with the same basicity is accompanied by a reduction to 10-30% aggressive effect of the slag on the periclase-carbon refractory. Slags with basicity 3-4, not containing magnesium oxide, are characterized at 1-4% B_2O_3 with a relatively low aggressive effect on periclase-carbon refractory. The wear degree of periclase-carbon refractory varies within 8-12% and practically does not reach 15%. Displacement of slags in the area increased to 5 basicity does not lead to a significant reduction in the aggressive impact on the refractory. The wear degree of the refractory sample varies in the range of 6-10% with a content of 1-4% B_2O_3 and increases to 15% with 5-6% B_2O_3 . It was noted that in order to ensure a lower aggressive effect of recommended composition slags, it is advisable to form them in the region of MgO saturation. The formation of such slags provides low viscosity and preservation of high refining properties.

References

- [1] D.A. Dyudkin, V.V. Kisilenko. Steel production. Volume 3. Out-of-furnace metallurgy of steel. *Moscow: Teplotekhnika*. **2010**. 544p. (russian)
- [2] S.M. Chumakov, A.M. Lamukhin, S.D. Zinchenko et al. The concept of low-sulfur steel production at OJSC Severstal taking into account technological aspects. *Proceedings of the Sixth Congress of Steelmakers. Chermetinformatsiya*. **2001**. No.3. P.63-66. (russian)
- [3] G.A. Sokolov. Out-of-furnace steel refining. *Moscow: Metallurgy*. **1977**. 208p. (russian)
- [4] W. Hongming, Z. Tingwang, Z. Hua. Effect of B_2O_3 on Melting Temperature, Viscosity and Desulfurization Capacity of CaO – based Refining Flux. *ISIJ International*. **2011**. Vol.51. No.5. P.702-708.
- [5] V.I. Kurpas, L.I. Krupman, S.S. Brodsky. Advanced technology of secondary refining of steel. *Sb.nauchn.-tech. articles from the magazine "Steel". Moscow: Metallurgy*. **1987**. P.61-64. (russian)

- EXPERIMENTAL STUDIES OF PERICLASE-CARBON REFRACTORIES SOLUBILITY IN THE SLAGS... 136-140
- [6] D. Takahashi, M. Kamo, Y. Kurose, H. Nomura. Deep steel desulphurisation technology in ladle furnace at KSC. *Ironmaking and Steelmaking*. **2003**. Vol.30. No.2. P.116-119.
- [7] P.K. Iwamasa, and R.J. Fruehan. Formation and behaviour of Mn containing oxysulphide inclusions during desulphurisation, deoxidation and alloying. *Metall. Mater. Trans. B*, **28**. **1997**. P.47.
- [8] P. Yan, X. Guo, S. Huang, J. Dyck, M. Guo, B. Blanpain. Desulphurisation of Stainless Steel by Using CaO–Al₂O₃ Based Slags during Secondary Metallurgy. *ISIJ International*. **2013**. Vol.53. No.3. P.459-467.
- [9] H. Gaye and J. Lehmann. Modeling and prediction of reactions involving metals, slags and fluxes. *VII International Conference on Molten Slags Fluxes and Salts. The South African Institute of Mining and Metallurgy*. **2004**. P.619-624.
- [10] Hui-xiang Yu, Xin-hua Wang, Mao Wang, Wan-jun Wang Desulfurization ability of refining slag with medium basicity. *Int. J. Miner. Metall. Mater.* **2014**. Vol.21. No.12. P.1160-1166.
- [11] A.A. Akberdin, I.S. Kulikov, V.A. Kim. Physical properties of melts of the system CaO-SiO₂-Al₂O₃-MgO-CaF₂. *Moscow: Metallurgy*. **1987**. 144p. (russian)
- [12] D.I. Povolotsky, V.E. Roshchin, V.P. Gribanov The influence of SiO₂ on the volatility of the slags of the CaF₂ – MgO – Al₂O₃ system. *Izvestiya VUZ. Ferrous metallurgy*. **1982**. No.8. P.39-42. (russian)
- [13] S.A. Istomin, E.A. Shepherds, V.M. Denisov. Physico - chemical properties of oxide - fluoride melts. *Ekaterinburg: Ural Branch of the Russian Academy of Sciences*. **2009**. 459p. (russian)
- [14] D.A. Dyudkin Steel production. The processes of smelting, secondary processing and continuous casting. Vol.1. *Moscow. Heat engineer*. **2008**. 528p. (russian)
- [15] A.A. Akberdin, G.M. Kireeva, I.A. Medvedovskaya. The effect of B₂O₃ on the viscosity of slags of the CaO – SiO₂ – Al₂O₃ system. *News of the USSR Academy of Sciences. Metals*. **1986**. No.3. P.55-56. (russian)
- [16] H. Wang, G. Li, R. Dai. CAS-OB refining slag modification with B₂O₃ – CaO and CaF₂ – CaO. *Ironmaking and Steelmaking*. **2007**. Vol.34. No.4. P.350-353.
- [17] A.A. Babenko, S.A. Istomin, E.V. Protopopov, A.V. Sychev, V.V. Ryabov. Viscosity of slags of the CaO-SiO₂-Al₂O₃-MgO-B₂O₃ system. *University news. Ferrous metallurgy*. **2014**. No.2. P.41-43. (russian)
- [18] V.A. Kim, A.A. Akberdin, I.S. Kulikov and others. The use of the simplex lattice method for the construction of diagrams of the composition-viscosity type. *University news. Ferrous metallurgy*. **1980**. No.9. P.167. (russian)
- [19] V.A. Kim, E.I. Nikolay, A.A. Akberdin, I.S. Kulikov. Planning an experiment in the study of the physicochemical properties of metallurgical slags: A methodological guide. *Alma-Ata: Science*. **1989**. 116p.
- [20] E. Shyurman, G. Mann, D. Nole, et al. Effect of dissolved MgO on the durability of the dolomite lining of oxygen converters. *Ferrous metals*. **1985**. No.3. P.33-41. (russian)
- [21] A.A. Babenco, A.G. Upolovnikova, and A.N. Smetannikov. Effects of slag basicity and B₂O₃ content on the viscosity of CaO-SiO₂-B₂O₃-25%Al₂O₃-8%MgO oxide system. *Butlerov Communications*. **2017**. Vol.50. No.4. P.117-122. ROI: jbc-02/17-50-4-117